

## Description

TOTAL Petrochemicals 529W is a medium flow crystal polystyrene specially formulated for mar resistance. This easy processing crystal grade minimizes visual defects from ejection and automated part handling. The unique molecular architecture maximizes part strength while maintaining excellent process performance. It is an economical alternative to SAN and polycarbonate.

## Applications

- Electronics
- Office accessories
- Appliance components

## General Information

- This material complies with FDA requirements as described in 21 CFR §177.1640.
- This material holds Underwriters Laboratory recognition 94HB; see UL File E55470 at [www.UL.com](http://www.UL.com).
- USP Class VI
- Material Safety Data Sheets are available to help customers satisfy their safety needs.

## Properties

Rheological Properties	ASTM Test	Unit	Typical Value
Melt Flow (200°C-5kg)	D-1238	g/10mn	3.5
<b>Thermal Properties</b>			
Heat Distortion - Annealed	D-648	°F	196
Vicat Softening	D-1525	°F	208
<b>Tensile Properties</b>			
Strength	D-638	psi	7,500
Modulus	D-638	psi (10 <sup>5</sup> )	4.3
<b>Flexural Properties</b>			
Strength	D-790	psi	14,000
Modulus	D-790	psi (10 <sup>5</sup> )	4.3
<b>Other Properties</b>			
Density		g/cm <sup>3</sup>	1.04
Linear Shrinkage	D-955	in/in	.004 - .007
Moisture		%	<0.1

10/2010

Polystyrene



TOTAL PETROCHEMICALS USA, INC.  
www.totalpetrochemicals.com  
1201 Louisiana Street  
Suite 1800  
Houston, TX 77002

CUSTOMER SERVICE  
P.O. Box 674411  
Houston, Texas 77267-4411  
Phone: 1-800-344-3462  
Fax: 713-483-5293

TECHNICAL CENTER  
P.O. Box 1200  
Deer Park, Texas 77536  
Phone: 281-884-7500  
Fax: 281-884-7576

**1-800-344-3462**

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of these products must be guided by the user's own methods for selection of proper formulation. TOTAL PETROCHEMICALS USA, INC. disclaims any responsibility for misuse or misapplication of its products. TOTAL PETROCHEMICALS USA, INC. MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL PETROCHEMICALS USA, INC. liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment no exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

