



TotalEnergies

TotalEnergies Petrochemicals & Refining USA, Inc.
Polymers Americas

Polystyrene 595T

Technical Data Sheet
Polystyrene - Crystal
Produced in the United States

Description

Polystyrene 595T: Is a high molecular weight, low melt flow, high heat crystal polystyrene specifically designed for direct injection foam operations to provide enhanced foam properties. It has higher melt strength than other high heat crystal resins in this melt flow range giving the converter the ability to reduce weight in their foam applications.

Application:

- Foam disposables
- Foam graphic art board
- Insulation foam board
- OPS disposables

General Information:

- This material complies with FDA requirements as described in 21 CFR §177.1640.
- Material Safety Data Sheets are available to help customers satisfy their safety needs.

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow (200°C-5kg)	D-1238	g/10mn	1.6
Mechanical Properties			
Tensile Strength	D-638	psi	7,700
Tensile Modulus	D-638	psi (10 ⁵)	4.4
Flexural Strength	D-790	psi	15,100
Flexural Modulus	D-790	psi (10 ⁵)	4.9
Thermal Properties			
Heat Distortion - Annealed	D-648	°F	211
Vicat Softening	D-1525	°F	225
Other Physical Properties			
Density		g/cm ³	1.04
Linear Shrinkage	D-955	in/in	.004 - .007
Moisture		%	<0.1

Rev: Sept 2021

Polystyrene

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA, Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

