

Description

HDPE 2004 TN52 is a high density polyethylene (HDPE) intended for the extrusion of corrugated pipes.

HDPE 2004 TN52 is best processed between 190 and 230°C

Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	g/cm ³	0.954
Melt Flow Rate (190°C/21.6 kg)	ISO 1133	g/10 min	22

(*) Data not intended for specification purposes

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website:

