

Description

HDPE 7195: Medium molecular weight, narrow molecular weight distribution, designed for high speed orientation.

Applications: Monofilament, slit tape, woven and knitted fabrics, specialty films.

Characteristics

	Method	Unit	Typical Value
Rheological Properties⁽¹⁾			
Melt Flow Index	D-1238	g/10 min	
190°C/2.16 kg			0.55
190°C/5 kg			1.9
Mechanical Properties⁽¹⁾⁽²⁾			
Tensile Strength @ Yield	D-638, Type IV specimen, 2 in/min	psi	3200
Elongation at Break	D-638, Type IV specimen, 2 in/min	%	>500
Secant Modulus of Elasticity @ 2% strain	D-638, Type IV specimen, 2 in/min	psi	100,000
Flexural Modulus	D-790	psi	115,000
Thermal Properties⁽¹⁾			
Melting Point	D-3417	°F	257
Other Physical Properties			
Density	D-792	g/cm ³	0.946

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) The data listed was determined on compression molded specimens and may, therefore, deviate from molded and extruded specimens.

HDPE 7195 06/2015



TOTAL PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
www.totalrefiningchemicals.com
 1201 Louisiana Street
 Suite 1800
 Houston, TX 77002

TECHNICAL CENTER
 P.O. Box 1200
 Deer Park, Texas 77536
 Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS & REFINING USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

