

Description

HDPE HL 428: Excellent processability, good tear and impact strength, good stiffness, excellent compatability with LDPE and LLDPE, Excellent drawdown, good moisture barrier properties.

Applications: Multi-wall liner, gas flush poultry bags, mailing envelopes, heavy-duty shipping sacks, fresh cut produce packaging, coextrusions.

Characteristics

	Method	Unit	Typical Value
Rheological Properties⁽¹⁾			
Melt Flow Index	D-1238	g/10 min	
190°C/2.16 kg			.28
190°C/21.6 kg (HLMI)			20.0
Mechanical Properties⁽¹⁾⁽²⁾			
Dart Impact	D1709, A	g	<50
Elmendorf Tear	D1922	g (MD/TD)	10 / 1450
Tensile Strength @ Yield	D-882, A	psi (MD/TD)	3400 / 3800
Tensile Strength @ Break	D-882, A	psi (MD/TD)	9000 / 2700
Elongation at Break	D-882, A	% (MD/TD)	450 / 600
1% Secant Modulus	D-882, A	kpsi (MD/TD)	103 / 145
WVTR ⁽³⁾	F1249	g/100in ² /day	0.7
High Stalk Extrusion⁽⁴⁾			
Dart Impact	D1709, A	g	100
Elmendorf Tear	D1922	g (MD/TD)	28 / 530
Tensile Strength @ Yield	D-882, A	psi (MD/TD)	3500 / 3700
Tensile Strength @ Break	D-882, A	psi (MD/TD)	7900 / 5700
Elongation at Break	D-882, A	% (MD/TD)	600 / 700
WVTR ⁽³⁾	F1249	g/100in ² /day	0.5
Thermal Properties			
Melting Point	D3417	°F	267
Processing Recommendation			
Extrusion Melt Temperature		°F	380-420
Other Physical Properties			
Density	D-792	g/cm ³	0.947

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) Film was produced at 1.0 mil with a 2.5 BUR.

(3) Water Vapor Transmission Rate

(4) Film was produced at 1.0 mil with a 6:1 FLH/D ratio and 4:1 BUR.

HDPE HL 428 06/2015



TOTAL PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
www.totalrefiningchemicals.com
1201 Louisiana Street
Suite 1800
Houston, TX 77002

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS & REFINING USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

