

Description

HDPE HL 535: High stiffness, good heat resistance, excellent bubble stability, good compatibility with LDPE and LLDPE

Applications: HL 535 is recommended for release liners, stand-up bags, coextruded films

Characteristics

	Method	Unit	Typical Value
Rheological Properties⁽¹⁾			
Melt Flow Index	D-1238	g/10 min	
190°C/2.16 kg			0.35
190°C/21.6 kg (HLMI)			30.0
Mechanical Properties⁽¹⁾⁽²⁾			
Dart Impact	D-1709, A	g	<50
Elmendorf Tear	D-1922	g (MD/TD)	8 / 1100
Tensile Strength @ Yield	D882, A, 20 in/min	psi (MD/TD)	4000 / 4300
Tensile Strength @ Break	D-882, A, 20 in/min	psi (MD/TD)	6300 / 4300
Elongation at Break	D-882, A, , 20 in/min	% (MD/TD)	500 / 25
1% Secant Modulus	D-882, A, , 20 in/min	kpsi (MD/TD)	133 / 186
WVTR ⁽³⁾ @ 100°F	F-1249	g/100in ² /day	0.7
Thermal Properties⁽¹⁾			
Melting Point	D-3417	°F	270
Other Physical Properties			
Density	D-792	g/cm ³	0.955
Processing Recommendation			
Extrusion Melt Temperature		°F	380 – 420

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(2) Film was produced at 1.0 mil with a 2.5 BUR.

(3) Water Vapor Transmission Rate

HDPE HL 535 06/2015



TOTAL PETROCHEMICALS & REFINING USA, INC.
 POLYMERS AMERICAS
www.totalrefiningchemicals.com
 1201 Louisiana Street
 Suite 1800
 Houston, TX 77002

TECHNICAL CENTER
 P.O. Box 1200
 Deer Park, Texas 77536
 Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TOTAL products must be guided by the users own methods for selection of proper formulation. TOTAL PETROCHEMICALS & REFINING USA, INC. disclaims any responsibility for misuse or miss application of its products. TOTAL MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TOTAL'S liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.

