

Description

Lumicene® mPE M 3509 is a metallocene-based medium density polyethylene (MDPE) combining the features of conventional blow molding polyethylene with differentiated optical properties such as gloss and contact clarity.

In combination with HDPE BM593 (physical blend), Lumicene® mPE M 3509 combines all the current requirements for the manufacture of blow molded packaging in the cosmetics and household liquids markets.

Lumicene® mPE M3509 is a pellet grade and contains antioxidants.

Characteristics

Property	Method	Unit	Typical value (*)
Density	ISO 1183	kg/m ³	935
Melt Flow Rate (190°C/2.16 kg)	ISO 1133/D	g/10 min	0.9
ESCR Antarox 100%	ASTM D 1693B	h	F ₅₀ > 1000
Notched Charpy Impact Resistance 23°C	ISO 179-1	kJ/m ²	80

(*) Data not intended for specification purposes

Processing

Lumicene® mPE M 3509 is best processed between 160 and 200°C in mono layer applications and at temperature between 180 and 220°C in coextrusion with HDPE BM 593.

Handling and storage

Please refer to the safety data sheet (SDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the SDS of our product. SDS may be obtained from the website: www.totalrefiningchemicals.com

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.

