



## Description

Lumicene Supertough® 20ST20 is a polyethylene film grade that is especially designed to have an excellent processability in cast extrusion and to give very high “toughness – holding” force balance allowing new innovative multilayer film concepts. Thanks to this innovative design, Lumicene Supertough® 20ST20 allows creation of added value in the film market.

## Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm <sup>3</sup>	0.920
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	1.8
Melting temperature	ISO 11357	°C	112
Vicat temperature	ISO 306	°C	106

*Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.*

## Processing

On a cast film line Lumicene Supertough 20ST20® are typically extruded in the following conditions:

- Melt Temperature: 220 to 280°C
- Chill roll temperature: 20 to 80°C

## Additives

Antioxidant : yes

Polymer Processing Aid : no





## Cast film properties

These values have been measured on a 20 µm cast film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD(**)	ISO 527-3	MPa	7.8 / 7.7
Tensile Strength at Break MD/TD(**)	ISO 527-3	MPa	37 / 39
Elongation at Break MD/TD(**)	ISO 527-3	%	379 / 610
Elmendorf MD/TD(**)	ISO 6383-2	N/mm	40 / 140
Dart test	ISO 7765-1	g	1100

(\*) Figures stated here above are obtained using laboratory test specimens produced at the following extrusion conditions: die gap = 250 µm, chill roll temperature = 20°C, throughput = 7 kg/h, melt temperature = 260 °C

(\*\*) MD : Machine Direction ; TD : Transverse Direction

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.

