

Description

Lumicene Supertough® 33ST22 is a metallocene polyethylene film grade that is especially designed to have an excellent tear resistance and to give a very high toughness – stiffness balance allowing new innovative multilayer film concepts. Thanks to its innovative design, Lumicene Supertough® 33ST22 will boost the mechanical properties of your packaging, including a superb tear resistance and excellent impact resistance.

Characteristics

Property	Method	Unit	Typical value
Density	ISO 1183	g/cm ³	0.933
Melt Flow Rate (190°C/2.16 kg)	ISO 1133	g/10 min	2.2
Melting temperature	ISO 11357	°C	122
Vicat temperature	ISO 306	°C	114

Values indicated are typical for this product. Density and MFR are properties routinely measured during "the standard quality control procedure". The other figures are generated by tests not included in the "standard quality control procedure", and are given for information only. Data are not intended for specification purposes.

Processing

Lumicene Supertough® 33ST22 has an excellent processability.

On a cast film line Lumicene Supertough® 33ST22 is recommended to be processed in the following conditions:

- Melt Temperature: 220 to 280°C
- Chill roll temperature: 20 to 80°C

Additives

Antioxidant : yes
 PPA : no

Information contained in this publication is true and accurate at the time of publication and to the best of our knowledge. The nominal values stated herein are obtained using laboratory test specimens. Before using one of the products mentioned herein, customers and other users should take all care in determining the suitability of such product for the intended use. Unless specifically indicated, the products mentioned herein are not suitable for applications in the pharmaceutical or medical sector. The Companies within Total Petrochemicals do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein. No information contained in this publication can be considered as a suggestion to infringe patents. The Companies disclaim any liability that may be claimed for infringement or alleged infringement of patents.



Cast film properties

These values have been measured on a 20 µm cast film.

Property	Method	Unit	Typical value (*)
Tensile Strength at Yield MD/TD (**)	ISO 527-3	MPa	12/12
Tensile Strength at Break MD/TD (**)	ISO 527-3	MPa	27/21
Elongation at Break MD/TD (**)	ISO 527-3	%	370/490
Elmendorf MD/TD (**)	ISO 6383-2	N/mm	70/200
Dart test	ISO 7765-1	g	90
Haze	ISO 14782	%	4
Gloss 45°	ASTM D2457		77

(*) Figures stated hereabove are obtained using laboratory test specimens produced at the following extrusion conditions: die gap = 250 µm, chill roll temperature = 20°C, throughput = 7 kg/h, melt temperature = 260 °C

(**) MD : Machine Direction, TD : Transverse Direction

