

## Description

TPSeal® M4741UV is a new generation metallocene High Density Polyethylene (mHDPE) with hexene as comonomer.

TPSeal® M4741UV is intended for the manufacture of rotomoulded items and available in natural, in pellets or in powder.

## Main Characteristics

Its specific molecular structure ensures:

- ✓ Superior mechanical properties
- ✓ Improved dimensional stability
- ✓ Easy processing
- ✓ Outstanding ESCR
- ✓ UV protected

## Application

Suitable for the production of tanks, underground tanks, kayaks, technical parts.

## Properties

Property	Method	Unit	Typical value (*)
Density (**)	ISO 1183	g/cm <sup>3</sup>	<b>0.947</b>
Melt Flow Rate (190°C-2.16kg)	ISO 1133/D	g/10min	<b>3.8</b>
Melting Temperature	ISO 11357	°C	<b>128</b>
Vicat Softening Point (Method A50)	ISO 306	°C	<b>120</b>
Heat Deflection Temperature (Method B)	ISO 75	°C	<b>70</b>
Tensile modulus	ISO 527	MPa	<b>970</b>
Tensile strength @yield	ISO 527	MPa	<b>23</b>
ESCR (10% Igepal)	ASTM D1693	h (F50)	<b>&gt; 1000</b>

(\*) Data not intended for specification purposes

(\*\*) Based on natural resin

## Processing conditions

It is recommended to keep product dry prior use for production.

## Handling and storage

Please refer to the material safety data sheet (MSDS) for handling and storage information. It is advisable to convert the product within one year after delivery provided storage conditions are used as given in the MSDS of our product.

