

A high hardness, multi-purpose thermoplastic elastomer featuring excellent compression set and high temperature performance. Sarlink® 3140 can be processed by injection molding or extrusion for applications such as grips, seals, gaskets, profiles and other articles.

Typical Properties*	Test Method	S.I.		U.S.	
		Typical Value	Units	Typical Value	Units
<b>Hardness shore A (5 sec)</b> Injection moulded sample Extruded sample	ASTM D-2240 5 sec. delay 5 sec. delay	46 40		46 40	
<b>Specific gravity</b>	ASTM D-792	0.93		0.93	
<b>Stress/strain properties</b> <u>Flow direction</u> Tensile strength Modulus 100% Elongation at break <u>Cross direction</u> Tensile strength Modulus 100% Elongation at break	ASTM D-412 Die C	2.6 1.3 328 3.8 1.02 552	MPa MPa % MPa MPa %	377 189 328 551 145 552	Psi Psi % Psi Psi %
<b>Tear strength</b> <u>Cross direction</u> Unnicked	ASTM D-624 Die C	16	kN/m	91	Pli
<b>Compression set</b> 22h/23°C 22h/70°C 22h/100°C	ASTM D-395 Method B	32 34 42	% % %	32 34 42	% % %
<b>Hot air aging</b> <u>168h/150°C, Cross Direction</u> Change in hardness Retention tensile strength Retention modulus at 100% Retention elongation at break <u>1000h/125°C, Cross Direction</u> Change in hardness Retention tensile strength Retention modulus at 100% Retention elongation at break	ASTM D-573	1.2 111 106 107 3.4 103 106 110	- % % % - % % %	1.2 111 106 107 3.4 103 106 110	- % % % - % % %
<b>Volume swell</b> 24h/121°C Oil #3 70h/125°C Oil #3	ASTM D-471	135 133	% %	135 133	% %
<b>Rheology</b> <u>Apparent Shear Viscosity</u> @ 206 1/s, 200°C	ASTM D-3835	254	Pa.s	254	Pa.s

\* Tests are conducted on injection moulded plaques unless indicated otherwise.

All information supplied by or on behalf of DSM in relation to its products, whether in of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence hereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or products, whose quality and other properties he shall verify, or any consequences thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party intellectual, industrial or other property by reason of application, processing or use of the aforementioned information or products by the buyer.

Sarlink® 3140 is a polypropylene based elastomer, which can be processed on conventional thermoplastic equipment for injection molding and extrusion. This product has a wide processing window in most applications. Melt temperatures from 360°-430°F can be used. Do not exceed 450°F. Drying is recommended for extrusion and blow molding and any time the material is used from an unsealed package. Dry three (3) hours at 180°F.

INJECTION MOULDING CONDITIONS			EXTRUSION CONDITIONS		
Melt temperature		360-430°F	Melt temperature		380-420°F
Barrel Temperatures	Rear	350-420°F	Barrel Temperatures	Rear	360-400°F
	Middle	350-420°F		Transition	360-400°F
	Front	350-420°F		Metered	370-410°F
	Nozzle	370-430°F		Front	370-410°F
			Die	380-420°F	
Mold Temperature		50-150°F			
Screw Speed		100-200 RPM	Roll Temperatures		70-120°F
Back Pressure		10-150 psi	Screen Pack		20 to 60 mesh
Screw	General Purpose 20:1 L/D ratio		Screw	General Purpose 3:1 compression ratio	

#### PURGING

Sarlink® 3140 has excellent melt stability. Empty the barrel for idle periods of thirty (30) minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene.

#### RECYCLING/REGRIND

This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing.

#### COLORING

The use of polyolefin based color concentrates is recommended. Apply back pressure in injection molding prior to disperse color.

#### BONDING/ASSEMBLY

Thermal bonding techniques can be used to form high strength bonds. Adhesive bonding can be achieved with specialized adhesives. Bond strength is limited due to the polypropylene base of this material.

#### STORAGE & HANDLING

Sarlink® 3140 is available in 55 lb. foil lined bags (up to 2,200 lbs. per pallet) or 1,100 lb. polyethylene lined gaylords. It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling.

DSM Thermoplastic Elastomers Inc. is an ISO 9001 registered company

Sarlink® is a registered trademark of DSM, The Netherlands

DSM Thermoplastic Elastomers B.V.  
P.O. Box 43  
NL-6130 AA Sittard  
The Netherlands  
Tel. +31 (0)46 4763037  
Fax. +31 (0)46 4760040  
Telex 36777

DSM Thermoplastic Elastomers Inc.  
31 Fuller Street  
Leominster, MA 01453  
USA  
Tel. (978) 534 1010  
Fax. (978) 534 1005  
Customer Service 1-800-524-0120