

Technical data sheet

AWT 8/96 001/003



FRIANYL A63 V0

Nylon 6.6 for injection moulding, flame retardant, free of halogen and phosphorus (rated UL 94 V0).

	Testing Standard	Unit	Values
Product Features			
Abbreviation	ISO 1043	--	----
Density	ISO 1183	g/cm ³	1.14
Viscosity index	ISO 307	ml/g	145
Water absorption at saturation (+23 °C)	ISO 62	%	8-9
Water absorption (+23 °C)	ISO 62	%	2,2-3,0
Shrinkage longitudinal	ISO 294-4 **	%	1,6-1,8
Shrinkage transvers	ISO 294-4 **	%	1,6-1,8
Material Constants for Flammability			
Flammability	UL-94	HB-V0	V0
Automobile interior fittings: thickness =1mm	FMVSS 302	----	----
Glow Wire GWFI	DIN EN 60695-2-12	----	----
Glow Wire GWIT	DIN EN 60695-2-13	----	----
Mechanical features			
Tensile modulus	ISO 527	N/mm ²	3500
Tensile strength	ISO 527	N/mm ²	80
Tensile elongation at break	ISO 527	%	5
Flexural strength	ISO 178	N/mm ²	102
Charpy impact (+23 °C)	ISO 179/1eU	kJ/m ²	NB
Charpy impact (-30 °C)	ISO 179/1eU	kJ/m ²	---
Charpy impact, notched (+23 °C)	ISO 179/1eA	kJ/m ²	4
Charpy impact, notched (-30 °C)	ISO 179/1eA	kJ/m ²	---
Surface hardness	ISO 2039-1	N/mm ²	150
Thermal features			
Melting point	ISO 3146 DSC	°C	256
Distorsion temp. under load (Meth. A)	ISO 75	°C	85
Distorsion temp. under load (Meth. B)	ISO 75	°C	185
Temp. index applied to 50% falling of tensile strength after 20 000h	IEC 216-1	°C	125
Electrical features			
Volume resistivity	IEC 60093	OHM cm	1 E 15
Surface resistivity	IEC 60093	OHM	----
Dissipation factor (1MHz)	IEC 250	----	0,02
Comparative figure of tracking CTI 50 drops	IEC 60112	----	----
Tracking index (CTI 100)	IEC 112	----	600
Comparative figure of tracking CTI-M 50 drops	IEC 60112	----	----
Tracking index (CTI-M 100)	IEC 112	----	600

* All values freshly molded, for variations please look in the product description

** Plate 60x60x2mm

Our publications, leaflets and technical data are for information and advice. Therefore no obligation can be derived from it. Please adapt the processing and application of the products to the prevailing conditions.

Revision : 22.11.2002

Technical data sheet

AWT 8/96 001/003



Product

FRIANYL A63 V0

Applications

Parts for the electrical-, construction- and traffic industry which need an official UL-94 authorization.

Processing Guidelines

Recommended material temperature 260-290°C, mold temperature 60-80°C, granular clamp <0,1%. Build-up pressure about 5-10bar hydraulic pressure. Please read our brochure "Processing guidelines of injection molding" for further information.

Pre-Treatment and Drying

The moisture proof and vacuum packed PA-granular can usually be processed without any special pre-treatment, except for large packages. The drying time depends on the humidity. We recommend at about 0,2% humidity a drying time of 4-8 hours at 80°C. The maximum humidity for injection molding should be less than 0,15%, of sensitive parts less than 0,1%. FRIANYL-granulars are packed with a residual moisture content of <0,15%.

Post-Treatment and conditioning

Our PA-types must be annealed to achieve their specific characteristics. The conditions should be the same as of the surroundings of the end product. Usually the humidity at standard conditioning atmosphere is about 1,5-2,5%, at immersion in water 7-9%. There might be slight changes like a volume- or longitudinal increase of about 0,1-0,3%/ per weight percentage of type and process. Attention to the changing shrinkage at an additional heat treatment.

Our publications, leaflets and technical data are for information and advice. Therefore no obligation can be derived from it. Please adapt the processing and application of the products to the prevailing conditions.

Revision : 22.11.2002