

Technical Data Sheet

Admex™ 334F Polymeric Plasticizer

Applications

- Caps & lids food contact

Product Description

Admex™ 334F is a polyester-type permanent plasticizer well-suited for critical uses where the PVC compound must be approved for food contact applications. Admex™ 334F has extraction and migration resistance superior to monomeric plasticizers suitable for these applications.

Typical Properties

Property	Typical Value, Units
General	
Acid Number	2 max.
Color Pt-Co	90 max.
Refractive Index @ 25°C	1.465
Specific Gravity @ 20°C/20°C	1.08
Boiling Point	>482 °F (>250 °C)
Flash Point Setaflash Closed Cup	448 °F (231 °C)
Pour Point	37 °F (3 °C)
Vapor Pressure @ 20°C	0.000001 torr (<0.0001 Pa)
Viscosity @ 25°C	3000-4200 cP (3000-4200 mPa·s)
@ 95°C	185 cP (185 mPa·s)
Wt/Vol @ 20°C	9.01 lb/gal (1.08 kg/L)

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.