



# Technical Data Sheet Admex™ 6995 Polymeric Plasticizer

### **Applications**

- Adhesives/sealants-b&c
- Automotive

# **Product Description**

Admex<sup>™</sup> 6995 is a medium molecular weight, light colored, polymeric adipate with a mild ester odor. Admex<sup>™</sup> 6995 is especially effective in highly filled automotive plastisols due to its permanence and toughness.

#### **Typical Properties**

Property	Typical Value, Units
General	
Acid Number	2 max.
Color Pt-Co	150
Refractive Index	
@ 25°C	1.47
Specific Gravity	
@ 20°C/20°C	1.09
Boiling Point	>572 °F (>300 °C)
Flash Point	
Setaflash Closed Cup	480 °F (249 °C)
Pour Point	10 to -15 °F (-12 to -26 °C)
Vapor Pressure	
@ 20°C	0.000001 torr (<0.0001 Pa)
Viscosity	
@ 25°C	1200-1600 cP (1200-1600 mPa·s)
@ 95°C	85 cP (85 mPa·s)
Wt/Vol	
@ 20°C	9.1 lb/gal (1.09 kg/L)

#### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.