

# Technical Data Sheet

## Admex™ 760 Polymeric Plasticizer

### Applications

- Graphic arts

### Product Description

Admex™ 760 is an ultra-high molecular weight, polymeric adipate. It possesses maximum resistance to extraction, migration and volatility.

### Typical Properties

Property	Typical Value, Units
<b>General</b>	
Acid Number	4 max.
Color Pt-Co	500 max.
Refractive Index @ 25°C	1.47
Specific Gravity @ 20°C/20°C	1.15
Boiling Point	>572 °F (>300 °C)
Flash Point Setaflash Closed Cup	464 °F (240 °C)
Pour Point	35 °F (1.67 °C)
Vapor Pressure @ 20°C	0.000001 torr (<0.0001 Pa)
Viscosity @ 25°C	40000-60000 cP (40000-60000 mPa·s)
@ 95°C	1800 cP (1800 mPa·s)
Wt/Vol @ 20°C	9.6 lb/gal (1.15 kg/L)

### Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*