

Akulon® CO-KGV4 /A JN.00.86

PA6-GF20 FR

20% Glass Reinforced, Heat Stabilized, Flame Retardant (halogen- phosphorous-free)

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage [parallel]	1.1 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.1 / *	%	Sim. to ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	4800 / -	MPa	ISO 527-1/-2
Stress at break	63 / -	MPa	ISO 527-1/-2
Strain at break	3 / -	%	ISO 527-1/-2
Charpy notched impact strength (+23°C)	2 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.6 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	0.8 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	1.6 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	0.8 / -	mm	IEC 60695-2-13

Property Data (Provisional)

Akulon[®] CO-KGV4 /A JN.00.86

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Electrical properties	dry / cond		
Relative permittivity (100Hz)	4.3 / 10	-	IEC 60250
Relative permittivity (1 MHz)	3.8 / 3.9	-	IEC 60250
Dissipation factor (100 Hz)	130 / 3000	E-4	IEC 60250
Dissipation factor (1 MHz)	210 / 1000	E-4	IEC 60250
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	30 / 25	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	V	IEC 60112
Other properties	dry / cond		
Water absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	2 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183