

Akulon® Diablo HDT2500 BK00001

PA66-GF35

35% Glass Reinforced, Heat Stabilized

Print Date: 2019-08-14

Properties	Typical Data	Unit	Test Method
Mechanical properties	dry / cond		
Tensile modulus	11000 / 6500	MPa	ISO 527-1/-2
Stress at break	190 / 110	MPa	ISO 527-1/-2
Strain at break	3 / 5	%	ISO 527-1/-2
Flexural modulus	10500 / -	MPa	ISO 178
Flexural strength	290 / -	MPa	ISO 178
Tensile modulus (200°C)	3200	MPa	ISO 527-1/-2
Stress at break (200°C)	65	MPa	ISO 527-1/-2
Strain at break (200°C)	10	%	ISO 527-1/-2
Charpy impact strength (+23°C)	80 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	240 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	258 / *	°C	ISO 75-1/-2
Other properties	dry / cond		
Water absorption	5 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183
Material specific properties	dry / cond		
Viscosity number	135 / *	cm ³ /g	ISO 307, 1157, 1628