

Akulon® Diablo HT-HG6

(PA66+PA6)-GF30

30% Glass Reinforced, Heat Stabilized

Print Date: 2019-06-05

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	9800 / 5500	MPa	ISO 527-1/-2
Stress at break	185 / 95	MPa	ISO 527-1/-2
Strain at break	3.1 / 6.5	%	ISO 527-1/-2
Flexural modulus	9000 / -	MPa	ISO 178
Flexural strength	270 / -	MPa	ISO 178
Charpy impact strength (+23°C)	60 / 85	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	55 / 55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	10 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	235 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	255 / *	°C	ISO 75-1/-2
Other properties	dry / cond		
Water absorption	6.9 / *	%	Sim. to ISO 62
Humidity absorption	2.4 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m ³	ISO 1183