

Akulon® F150-CZ

PA6

Very High Viscosity, Food Contact Quality, Lubricated

Print Date: 2019-07-24

Properties	Typical Data	Unit	Test Method
Mechanical properties dry / cond			
Tensile modulus	3200 / -	MPa	ISO 527-1/-2
Nominal strain at break	>50 / -	%	ISO 527-1/-2
Yield stress	85 / -	MPa	ISO 527-1/-2
Yield strain	4 / -	%	ISO 527-1/-2
Thermal properties dry / cond			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion (parallel)	1 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Electrical properties dry / cond			
Relative permittivity (100Hz)	3.4 / -	-	IEC 60250
Relative permittivity (1 MHz)	3.1 / -	-	IEC 60250
Dissipation factor (100 Hz)	65 / -	E-4	IEC 60250
Dissipation factor (1 MHz)	165 / -	E-4	IEC 60250
Volume resistivity	1E13 / -	Ohm*m	IEC 60093
Surface resistivity	- / 1E15	Ohm	IEC 60093
Electric strength	25 / -	kV/mm	IEC 60243-1
Other properties dry / cond			

Property Data

Akulon[®] F150-CZ

Print Date: 2019-07-24

Properties	Typical Data	Unit	Test Method
Water absorption	9.5 / *	%	Sim. to ISO 62
Humidity absorption	2.5 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183
Material specific properties	dry / cond		
Viscosity number	370 / *	cm ³ /g	ISO 307, 1157, 1628