

## Akulon® F232-D

## PA6

High Viscosity

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
<b>Mechanical properties</b> dry / cond			
Tensile modulus	3300 / -	MPa	ISO 527-1/-2
Nominal strain at break	35 / -	%	ISO 527-1/-2
Yield stress	85 / -	MPa	ISO 527-1/-2
Yield strain	4 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	7 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / -	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b> dry / cond			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	160 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.4 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
<b>Electrical properties</b> dry / cond			
Relative permittivity (100Hz)	3.9 / 14	-	IEC 60250
Relative permittivity (1 MHz)	3.4 / 4.5	-	IEC 60250

Akulon<sup>®</sup> F232-D

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Dissipation factor (100 Hz)	110 / 3000	E-4	IEC 60250
Dissipation factor (1 MHz)	220 / 1200	E-4	IEC 60250
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 60093
Surface resistivity	* / 1E14	Ohm	IEC 60093
Electric strength	27 / 20	kV/mm	IEC 60243-1
Comparative tracking index	600 / 600	V	IEC 60112
<b>Other properties</b>	<b>dry / cond</b>		
Water absorption	10 / *	%	Sim. to ISO 62
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183
<b>Material specific properties</b>	<b>dry / cond</b>		
Viscosity number	214 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628