

Akulon® K222-KGV6

PA6-GF30 FR(30)

30% Glass Reinforced, Heat Stabilized, Flame Retardant (halogen- phosphorous-free)

Print Date: 2019-08-15

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.55 / *	%	ISO 294-4
Molding shrinkage (normal)	0.9 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	6900 / 3200	MPa	ISO 527-1/-2
Stress at break	80 / 48	MPa	ISO 527-1/-2
Strain at break	3.6 / 25	%	ISO 527-1/-2
Charpy impact strength (+23°C)	43 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	180 / *	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	1.6 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	0.75 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	750 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	1.6 / -	mm	IEC 60695-2-13

Property Data

Akulon[®] K222-KGV6

Print Date: 2019-08-15

Properties	Typical Data	Unit	Test Method
Glow Wire Ignition Temperature GWIT	775 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	0.75 / -	mm	IEC 60695-2-13
Electrical properties	dry / cond		
Comparative tracking index	525 / -	V	IEC 60112
Other properties	dry / cond		
Water absorption	5.6 / *	%	Sim. to ISO 62
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1440 / -	kg/m ³	ISO 1183