

Akulon® K223-TP4

PA6-I

Impact Modified

Print Date: 2019-08-15

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	1.4 / *	%	ISO 294-4
Molding shrinkage (normal)	1.7 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	2000 / 625	MPa	ISO 527-1/-2
Nominal strain at break	>50 / >50	%	ISO 527-1/-2
Yield stress	50 / 30	MPa	ISO 527-1/-2
Yield strain	4 / 30	%	ISO 527-1/-2
Flexural modulus	1600 / -	MPa	ISO 178
Flexural strength	65 / -	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	65 / 75	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	18 / 25	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Temp. of deflection under load (1.80 MPa)	55 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	130 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	1.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.2 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	700 / -	°C	IEC 60695-2-12

Akulon[®] K223-TP4

Print Date: 2019-08-15

Properties	Typical Data	Unit	Test Method
GWFI (Thickness (1) tested)	2 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	700 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	1.5 / -	mm	IEC 60695-2-12
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	2 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	725 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	1.5 / -	mm	IEC 60695-2-13

Electrical properties

dry / cond

Relative permittivity (100Hz)	3.1 / 10	-	IEC 60250
Relative permittivity (1 MHz)	2.7 / 3.5	-	IEC 60250
Dissipation factor (100 Hz)	30 / 1600	E-4	IEC 60250
Dissipation factor (1 MHz)	160 / 1000	E-4	IEC 60250
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 60093
Surface resistivity	- / 5E14	Ohm	IEC 60093
Electric strength	27 / 20	kV/mm	IEC 60243-1
Comparative tracking index	* / 600	V	IEC 60112

Other properties

dry / cond

Water absorption	8.5 / *	%	Sim. to ISO 62
Humidity absorption	2.3 / *	%	Sim. to ISO 62
Density	1070 / -	kg/m ³	ISO 1183