

Akulon® K224-G4U

PA6-GF23

23% Glass Reinforced

Print Date: 2019-01-29

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.25 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	7500 / 4400	MPa	ISO 527-1/-2
Stress at break	130 / 52	MPa	ISO 527-1/-2
Strain at break	3.5 / 6	%	ISO 527-1/-2
Charpy impact strength (+23°C)	60 / 105	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	55 / 55	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6 / 10.5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	3.5 / 10.5	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.05 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.71 / *	mm	IEC 60695-11-10

Property Data

Akulon[®] K224-G4U

Print Date: 2019-01-29

Properties	Typical Data	Unit	Test Method
Other properties	dry / cond		
Water absorption	7 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1300 / *	kg/m ³	ISO 1183