

Akulon® K224-G8

PA6-GF40

40% Glass Reinforced

Print Date: 2019-04-03

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.34 / *	%	ISO 294-4
Molding shrinkage (normal)	0.83 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	13000 / 8000	MPa	ISO 527-1/-2
Stress at break	205 / 140	MPa	ISO 527-1/-2
Strain at break	3 / 6	%	ISO 527-1/-2
Flexural modulus	10800 / -	MPa	ISO 178
Flexural strength	275 / -	MPa	ISO 178
Charpy impact strength (+23°C)	95 / 100	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	85 / 85	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 22	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 13	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.5 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10

Akulon[®] K224-G8

Print Date: 2019-04-03

Properties	Typical Data	Unit	Test Method
Thickness tested	0.71 / *	mm	IEC 60695-11-10
Electrical properties	dry / cond		
Relative permittivity (100Hz)	3.5 / 14	-	IEC 60250
Relative permittivity (1 MHz)	3.3 / 4.4	-	IEC 60250
Dissipation factor (100 Hz)	50 / 3000	E-4	IEC 60250
Dissipation factor (1 MHz)	150 / 1200	E-4	IEC 60250
Volume resistivity	>1E13 / 1E12	Ohm*m	IEC 60093
Surface resistivity	* / 1E13	Ohm	IEC 60093
Electric strength	35 / 25	kV/mm	IEC 60243-1
Comparative tracking index	* / 500	V	IEC 60112
Other properties	dry / cond		
Water absorption	5.5 / *	%	Sim. to ISO 62
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1450 / -	kg/m ³	ISO 1183