

Akulon® K224-HG7

PA6-GF35

35% Glass Reinforced, Heat Stabilized

Print Date: 2019-10-23

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	0.9 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	11500 / 7000	MPa	ISO 527-1/-2
Stress at break	195 / 125	MPa	ISO 527-1/-2
Strain at break	3.5 / 7	%	ISO 527-1/-2
Flexural modulus	9700 / -	MPa	ISO 178
Flexural strength	255 / -	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 100	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	75 / 75	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / 24	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12 / 12	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	15 / -	kJ/m ²	ISO 180/1A
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10

Akulon® K224-HG7

Print Date: 2019-10-23

Properties	Typical Data	Unit	Test Method
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.71 / *	mm	IEC 60695-11-10

Electrical properties

dry / cond

Relative permittivity (100Hz)	4.8 / -	-	IEC 60250
Relative permittivity (1 MHz)	4.3 / -	-	IEC 60250
Dissipation factor (100 Hz)	170 / -	E-4	IEC 60250
Dissipation factor (1 MHz)	220 / -	E-4	IEC 60250
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 60093
Surface resistivity	- / 1E13	Ohm	IEC 60093
Electric strength	35 / 25	kV/mm	IEC 60243-1
Comparative tracking index	* / 500	V	IEC 60112

Other properties

dry / cond

Water absorption	5.9 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1400 / -	kg/m ³	ISO 1183