

Akulon® N22D

PA6

Low Viscosity

Print Date: 2019-10-05

Properties	Typical Data	Unit	Test Method
Rheological properties	dry / cond		
Molding shrinkage (parallel)	1.2 / *	%	ISO 294-4
Molding shrinkage (normal)	1.2 / *	%	ISO 294-4
Mechanical properties	dry / cond		
Tensile modulus	2900 / -	MPa	ISO 527-1/-2
Nominal strain at break	10 / -	%	ISO 527-1/-2
Yield stress	65 / -	MPa	ISO 527-1/-2
Yield strain	3.5 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / -	kJ/m ²	ISO 179/1eA
Thermal properties	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Other properties	dry / cond		
Water absorption	9 / *	%	Sim. to ISO 62
Humidity absorption	2.5 / *	%	Sim. to ISO 62
Density	1120 / -	kg/m ³	ISO 1183