

Akulon® N24-G3

PA6-GF15

15% Glass Reinforced

Print Date: 2019-03-01

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	dry / cond		
Tensile modulus	5500 / -	MPa	ISO 527-1/-2
Stress at break	115 / -	MPa	ISO 527-1/-2
Strain at break	2.5 / -	%	ISO 527-1/-2
Charpy impact strength (+23°C)	35 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	6 / -	kJ/m ²	ISO 180/1A
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3