

Akulon® S223-HGo

PA66-GF50

50% Glass Reinforced, Heat Stabilized

Print Date: 2019-09-17

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.4 / *	%	ISO 294-4
Molding shrinkage (normal)	1.2 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	16800 / 11500	MPa	ISO 527-1/-2
Stress at break	245 / 170	MPa	ISO 527-1/-2
Strain at break	2.6 / 3.9	%	ISO 527-1/-2
Flexural modulus	14500 / -	MPa	ISO 178
Flexural strength	320 / -	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 94	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	97 / 101	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	16 / 21	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	14 / 14	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	253 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	260 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10

Akulon[®] S223-HGo

Print Date: 2019-09-17

Properties	Typical Data	Unit	Test Method
Other properties	dry / cond		
Water absorption	4.2 / *	%	Sim. to ISO 62
Humidity absorption	1.2 / *	%	Sim. to ISO 62
Density	1570 / -	kg/m ³	ISO 1183