

Akulon® SafeConnect SC21

PA66 FR(17)

Flame Retardant

Print Date: 2019-09-24

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	1.8 / *	%	ISO 294-4
Molding shrinkage (normal)	1.8 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	3600 / -	MPa	ISO 527-1/-2
Stress at break	80 / -	MPa	ISO 527-1/-2
Strain at break	11 / -	%	ISO 527-1/-2
Yield strain	4.3 / -	%	ISO 527-1/-2
Flexural modulus	3300 / -	MPa	ISO 178
Flexural strength	105 / -	MPa	ISO 178
Charpy impact strength (+23°C)	88 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	3.5 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	4.7 / -	kJ/m ²	ISO 180/1A
Thermal properties			
	dry / cond		
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-12
Glow Wire Flammability Index GWFI	960 / -	°C	IEC 60695-2-12
GWFI (Thickness (2) tested)	3 / -	mm	IEC 60695-2-12

Akulon[®] SafeConnect SC21

Print Date: 2019-09-24

Properties	Typical Data	Unit	Test Method
Glow Wire Ignition Temperature GWIT	960 / -	°C	IEC 60695-2-13
GWIT (Thickness (1) tested)	0.4 / -	mm	IEC 60695-2-13
Glow Wire Ignition Temperature GWIT	800 / -	°C	IEC 60695-2-13
GWIT (Thickness (2) tested)	3 / -	mm	IEC 60695-2-13
Electrical properties	dry / cond		
Comparative tracking index	250 / -	V	IEC 60112
Other properties	dry / cond		
Density	1340 / -	kg/m ³	ISO 1183