

Akulon® Ultraflow K-FHGR24

PA6-(GF+GB)30

10% Glass Reinforced, 20% Glass Beads Reinforced, Heat Stabilized, High Flow

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Mechanical properties dry / cond			
Tensile modulus	6000 / 3500	MPa	ISO 527-1/-2
Stress at break	85 / 55	MPa	ISO 527-1/-2
Strain at break	2.5 / 5	%	ISO 527-1/-2
Flexural modulus	4900 / 2300	MPa	ISO 178
Flexural strength	124 / 63	MPa	ISO 178
Charpy impact strength (+23°C)	21 / -	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	21 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / 4	kJ/m ²	ISO 179/1eA
Thermal properties dry / cond			
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.35 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.75 / *	mm	IEC 60695-11-10
Electrical properties dry / cond			
Relative permittivity (100Hz)	3.5 / 14	-	IEC 60250
Relative permittivity (1 MHz)	3.3 / 4.5	-	IEC 60250

Akulon[®] Ultraflow K-FHGR24

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
Dissipation factor (100 Hz)	50 / 3000	E-4	IEC 60250
Dissipation factor (1 MHz)	150 / 1200	E-4	IEC 60250
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 60093
Surface resistivity	* / 1E13	Ohm	IEC 60093
Electric strength	35 / 25	kV/mm	IEC 60243-1
Comparative tracking index	350 / 350	V	IEC 60112
Other properties	dry / cond		
Water absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1350 / -	kg/m ³	ISO 1183