

# Akulon® Ultraflow K-FKG6

## PA6-GF30

30% Glass Reinforced, Heat Stabilized, High Flow

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
<b>Rheological properties</b>			
	dry / cond		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
<b>Mechanical properties</b>			
	dry / cond		
Tensile modulus	9500 / 5700	MPa	ISO 527-1/-2
Stress at break	170 / 105	MPa	ISO 527-1/-2
Strain at break	3.5 / 7	%	ISO 527-1/-2
Flexural modulus	8600 / -	MPa	ISO 178
Flexural strength	235 / -	MPa	ISO 178
Charpy impact strength (+23°C)	85 / 90	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	65 / 65	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 22	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
	dry / cond		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10

# Akulon<sup>®</sup> Ultraflow K-FKG6

Print Date: 2018-12-13

Properties	Typical Data	Unit	Test Method
<b>Other properties</b>	<b>dry / cond</b>		
Water absorption	6 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1350 / -	kg/m <sup>3</sup>	ISO 1183