



Technical Data Sheet

Applications

Tires

Product Description

Chemical name: Mixture of polymeric sulfur and rhombic sulfur

Crystex™ 60 OT 10 is a non-blooming vulcanizing agent for unsaturated elastomers.

MAJOR APPLICATIONS AND PROPERTIES:

- Crystex™ 60 OT 10 is a mixture of polymeric sulfur and rhombic sulfur with limited solubility in elastomers.
 Consequently it will retard bin scorch, prevent migration of sulfur and preserve surface tack. This is important in the manufacture of tires and other plied-up rubber goods.
- At vulcanization temperatures Crystex[™] 60 OT 10 will de-polymerize to soluble sulfur and will behave similar to "Rubber Maker's" sulfur.
- Crystex[™] 60 OT 10 is a metastable product which can revert to soluble sulfur if not stored under proper conditions.
- Reversion of Crystex[™] 60 OT 10 to soluble sulfur is also catalyzed by alkaline products. The presence of alkaline accelerators can be critical.
- Crystex[™] 60 OT 10 is used in compounds containing a relatively large sulfur loading above the solubility of sulfur in the elastomer.
- Crystex[™] 60 OT 10 is non-staining and non-discoloring.

Typical Properties

Property	Typical Value, Units
General	
Form	Insoluble/ground sulfur mix (60/40), 10% oil treated powder
Specific Gravity @ 20°C	1.78
Bulk Density	
Packed	500-800 kg/m ³
Unpacked	250-450 kg/m ³
Mean particle size	<30 μm

Compounding Information

Because insoluble sulfur is metastable temperatures should be kept as low as possible during mixing. Between 100°C and 130° C significant reversion can take place to soluble sulfur.

Dispersion of Crystex™ 60 OT 10 in rubber is critical. Due to its small particle size and its tendency for electrostatic charge build-up, agglomerates can be formed which can result in inhomogeneous vulcanizates. Sufficiently long mixing times should be applied preferably in a separate mixing step under well controlled conditions.

If dry pre-mixes are produced of Crystex^M 60 OT 10 and other vulcanization chemicals, reversion can take place if Crystex^M 60 OT 10 is in direct contact with alkaline components.

Because Crystex[™] 60 OT 10 contains a relatively high soluble sulfur content, applications should be limited to compounds with a relatively low level of sulfur and/or low compounding temperature.

Handling Precautions

For detailed information on toxicological properties and handling precautions please refer to the current Safety Data Sheet. This information sheet can be downloaded from our web site or requested from the nearest Eastman office and should be consulted before handling this product.

Storage

Store CrystexTM in a well ventilated area below 30°C, avoiding exposure of the packaged product to direct sunlight. Do not store near products that can emit free amines such as sulfenamides and DTDM. Amines and other alkaline vapors can cause CrystexTM to revert to "Rubber Maker's" sulfur at any temperature. High temperatures will also cause CrystexTM to revert to "Rubber Maker's" sulfur. When stored in closed containers below 20°C the reversion rate is less than 1%/year. Reversion of CrystexTM could result in sulfur bloom of uncured rubber.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.