

Technical Data Sheet

Drystar™ 0603 Copolyester

Applications

- Appliances (food contact)
- Bottles-skin care pkg
- Color cosmetics packaging
- Consumer housewares-nfc
- Jars-skin care pkg
- Multi-layer film non food contact
- Personal care & cosmetics packaging
- Skin care packaging

Product Description

Eastman is pleased to announce the launch of DRYSTAR* copolyesters. This new product-line is designed to meet the needs of converters seeking value-added solutions to their drying requirements of copolyesters. Eastman's copolyesters are highly valued for their excellent balance of properties such as superior aesthetics, impact strength, and chemical resistance. These properties can be optimally realized when the resins are properly dehydrated in accordance to recommended drying conditions and equipment.

Recognizing this value, Eastman conceived Drystar™ copolyesters to allow converters with limited access to desiccant dryers to achieve these optimizations. In addition, some converters with desiccant dryers may still find Drystar™ copolyesters value-adding to attain production flexibility and cost saving by removing the drying process prior to injection molding, profile extruding, or extrusion blow molding copolyesters. The initial launch comprises of the commercialization of four grades of Drystar™ copolyesters and Eastman has on-going program to extend this strategic product-line in the future.

*DRYSTAR is only available in the Asia Pacific Region.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.27
Mold Shrinkage		
Parallel to Flow, 3.2-mm (0.125-in.) thickness	D 955	0.002-0.005 mm/mm (0.002-0.005 in./in.)
Mechanical Properties (ISO Method)		
Tensile Strength @ Yield	ISO 527	48 MPa
Tensile Strength @ Break	ISO 527	29 MPa
Elongation @ Yield	ISO 527	4 %
Elongation @ Break	ISO 527	200 %
Tensile Modulus	ISO 527	2000 MPa
Flexural Modulus	ISO 178	2100 MPa
Flexural Strength	ISO 178	67 MPa
Izod Impact Strength, Notched		
@ 23°C	ISO 180	9.4 kJ/m ²
@ -40°C	ISO 180	4.4 kJ/m ²
Mechanical Properties		
Tensile Stress @ Break	D 638	30 MPa (4300 psi)
		50 MPa (7200 psi)

Tensile Stress @ Yield	D 638	
Elongation @ Break	D 638	180 %
Elongation @ Yield	D 638	4.4 %
Tensile Modulus	D 638	2030 MPa (2.9 x 10 ⁵ psi)
Flexural Strength	D 790	68 MPa (9800 psi)
Flexural Modulus	D 790	2060 MPa (3.0 x 10 ⁵ psi)
Rockwell Hardness, R Scale	D 785	108
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	105 J/m (1.9 ft·lbf/in.)
@ -40°C (-40°F)	D 256	40 J/m (0.7 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	-NB
@ -40°C (-40°F)	D 4812	-NB
Optical Properties		
Haze	D 1003	0.2 %
Total Transmittance	D 1003	90 %
Thermal Properties (ISO Method)		
Deflection Temperature		
@ 0.455 MPa (66 psi)	ISO 75	70 °C
@ 1.82 MPa (264 psi)	ISO 75	62 °C
Thermal Properties		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	70 °C (158 °F)
@ 1.82 MPa (264 psi)	D 648	62 °C (143 °F)
Typical Processing Conditions		
Drying Temperature ^d		71 °C (160 °F)
Drying Time ^d		6 hrs
Processing Melt Temperature		249-271 °C (480-520 °F)
Mold Temperature		16-38 °C (60-100 °F)

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^dDrying is only recommended for products previously opened and exposed to humid conditions.

Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

5/29/2019 12:22:57 PM