

Technical Data Sheet

Drystar™ 0831 Copolyester

Applications

- Jars-skin care pkg
- Personal care & cosmetics packaging

Key Attributes

- High clarity and transparency
- High flow copolyester
- Tough

Product Description

Drystar™ 0831 Copolyester is a high flow product and contains a mold release. Other outstanding features of Drystar™ 0831 are easily maintained such as excellent appearance and clarity, good physical properties, chemical resistance, and easy processing. Drystar™ 0831 is for sale only in Asia as a high-flow formulation.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.27
Mold Shrinkage	D 955	0.002-0.005 mm/mm (0.002-0.005 in./in.)
Mechanical Properties		
Tensile Stress @ Yield	D 638	48 MPa (7000 psi)
Tensile Stress @ Break	D 638	24 MPa (3500 psi)
Elongation @ Yield	D 638	4 %
Elongation @ Break	D 638	75 %
Flexural Modulus	D 790	1900 MPa (2.76 x 10 ⁵ psi)
Flexural Strength	D 790	66 MPa (9600 psi)
Rockwell Hardness, R Scale	D 785	107
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	84 J/m (1.5 ft·lbf/in.)
@ -40°C (-40°F)	D 256	46 J/m (0.8 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	35 J (26 ft·lbf)
@ -40°C (-40°F)	D 3763	44 J (32 ft·lbf)
Optical Properties		
Haze	D 1003	0.4 %
Total Transmittance	D 1003	91 %
Thermal Properties		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	68 °C (154 °F)
@ 1.82 MPa (264 psi)	D 648	60 °C (140 °F)
Typical Processing Conditions		
Drying Temperature ^d		71 °C (160 °F)
Drying Time ^d		6 hrs
Processing Melt Temperature		249-271 °C (480-520 °F)
Mold Temperature		16-38 °C (60-100 °F)

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^dDrying is only recommended for products previously opened and exposed to humid conditions.

Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.