

DSM Engineering Plastics - Property Data

Arnitel® EM630-H

TPE-unfilled

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	4.7	cm ³ /10min	ISO 1133
Temperature	240	°C	ISO 1133
Load	2.16	kg	ISO 1133
MECHANICAL PROPERTIES			
Tensile modulus	310	MPa	ISO 527-1/-2
Stress at 10% strain	15.9	MPa	ISO 527-1/-2
Stress at 100% strain	15.8	MPa	ISO 527-1/-2
Charpy notched impact strength (+23°C)	N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	12	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
Melting temperature (10°C/min)	212	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	125	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	1.5	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	1.5	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.6 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
ELECTRICAL PROPERTIES			
Relative permittivity (1 MHz)	4.1	-	IEC 60250
Dissipation factor (1 MHz)	170	E-4	IEC 60250
Volume resistivity	1.20E11	Ohm*m	IEC 60093
Surface resistivity	2.50E14	Ohm	IEC 60093
Electric strength	22	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
OTHER PROPERTIES			
Density	1230	kg/m ³	ISO 1183
Water absorption	0.63	%	Sim. to ISO 62
Humidity absorption	0.18	%	Sim. to ISO 62

01.04.2004

DSM Product

Unlimited. DSM

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information.