

Technical Data Sheet

Eastar™ Copolyester DN003 Natural

Applications

- Filter housing

Key Attributes

- Chemical resistance to most medical solvents including lipids and IPA
- Easy to extrude, cut, print, and seal
- Effective barrier properties
- Excellent chemical resistance
- Excellent clarity
- Excellent colorability
- Gamma and E-beam color stability
- Good impact strength
- Good stiffness
- High gloss appearance
- Toughness

Product Description

Eastar™ Copolyester DN003 contains a mold release. It has excellent appearance and is nearly water-clear. This polymer is the toughest of the Eastar™ family of products. Additional outstanding features are chemical resistance and excellent color and property retention following gamma and e-beam sterilization.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED

The GREENGUARD INDOOR AIR QUALITY CERTIFIED Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit

. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General		
Specific Gravity	D 792	1.23
Water Absorption, 24 h immersion	D 570	0.13 %
	ISO 62	0.13 %
Mold Shrinkage Parallel to Flow, 3.2-mm (0.125- in.) thickness	D 955	0.002-0.005 mm/mm (0.002-0.005 in./in.)
Density	ISO 1183	1.23 g/cm ³
Mechanical Properties		
Tensile Stress @ Yield	D 638	45 MPa (6500 psi)
	ISO 527	46 MPa
Tensile Stress @ Break	D 638	52 MPa (7600 psi)
	ISO 527	47 MPa
Elongation @ Yield	D 638	5 %
	ISO 527	4.4 %
Elongation @ Break	D 638	330 %
	ISO 527	230 %

Flexural Modulus	D 790 ISO 178	1800 MPa (2.6 x 10 ⁵ psi) 1800 MPa
Flexural Yield Strength	D 790 ISO 178	66 MPa (9600 psi) 63 MPa
Rockwell Hardness, R Scale	D 785	105
Izod Impact Strength, Notched		
@ 23°C	ISO 180	125 kJ/m ²
@ 23°C (73°F)	D 256	NB
@ -40°C	ISO 180	7.4 kJ/m ²
@ -40°C (-40°F)	D 256	64 J/m (1.2 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	ISO 6603-2	14 J
@ -40°C (-40°F)	ISO 6603-2	16 J
Thermal Properties		
Deflection Temperature		
@ 0.45 MPa	ISO 75	74 °C
@ 0.455 MPa (66 psi)	D 648	74 °C (165 °F)
@ 1.80 MPa	ISO 75	65 °C
@ 1.82 MPa (264 psi)	D 648	64 °C (147 °F)
Vicat Softening Temperature		
@ 1 kg load	D 1525	88 °C (190 °F)
@ 1 kg load	ISO 306	88 °C
@ 5 kg load	ISO 306	79 °C
Thermal Conductivity		0.19 W/m·K (1.3 Btu·in./h·ft ² ·°F)
Specific Heat		
@ 240°C (464°F)	DSC	2.05 kJ/kg·K (0.49 Btu/lb·°F)
@ 60°C (140°F)	DSC	1.34 kJ/kg·K (0.32 Btu/lb·°F)
UL Flammability Classification		
1.6 mm (0.0625 in.) specimen	UL 94	94HB
3.2 mm (0.125 in.) specimen	UL 94	94HB
Typical Processing Conditions		
Drying Temperature		71 °C (160 °F)
Drying Time		6 hrs
Processing Melt Temperature		250-270 °C (480-520 °F)
Mold Temperature		15-40 °C (60-100 °F)

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

General

All ISO tests are run @ 4-mm thickness with the exception of Impact Resistance, which is run @ 2-mm thickness.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

© 2019 Eastman Chemical Company or its subsidiaries. All rights reserved. As used herein, ® denotes registered trademark status in the U.S. only.