

# Technical Data Sheet

## Eastar™ Copolyester MN006 Natural

### Applications

- Blood contact and dialysis
- Fluid administration
- Medical devices

### Key Attributes

- Chemical resistance to most medical solvents including lipids and IPA
- Gamma and E-beam color stability

### Product Description

Eastar™ Copolyester MN006 has been tested for FDA/ISO 10993 and USP Class VI Biological Evaluation testing after Gamma and EtO sterilization. Eastar™ Copolyester MN006 Natural is a brilliantly clear polymer having excellent impact strength, chemical resistance, and low shrinkage rates. Eastar™ Copolyester MN006 Natural contains a mold release. This polymer is the toughest of the Eastar™ family of products. Additional outstanding features are chemical resistance and excellent color and property retention following gamma and e-beam sterilization.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED

The GREENGUARD INDOOR AIR QUALITY CERTIFIED Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit [www.geiconsulting.com](#)

. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>General</b>		
Specific Gravity	D 792	1.23
Mold Shrinkage		
Parallel to Flow	D 955	0.002-0.005 mm/mm (0.002-0.005 in./in.)
<b>Mechanical Properties</b>		
Tensile Stress @ Yield	D 638	44 MPa (6300 psi)
Tensile Stress @ Break	D 638	54 MPa (7800 psi)
Elongation @ Yield	D 638	4 %
Elongation @ Break	D 638	330 %
Tensile Modulus	D 638	1800 MPa (2.6 x 10 <sup>5</sup> psi)
Flexural Modulus	D 790	1800 MPa (2.6 x 10 <sup>5</sup> psi)
Flexural Strength	D 790	66 MPa (9600 psi)
Rockwell Hardness, R Scale	D 785	105
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	NB
@ -40°C (-40°F)	D 256	77 J/m (1.4 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	46 J (34 ft·lbf)

@ -40°C (-40°F)	D 3763	46 J (34 ft·lbf)
<b>Optical Properties</b>		
Haze	D 1003	<1.0 %
Regular Transmittance	D 1003	89 %
Total Transmittance	D 1003	92 %
<b>Thermal Properties</b>		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	73 °C (163 °F)
@ 1.82 MPa (264 psi)	D 648	64 °C (147 °F)
<b>Typical Processing Conditions</b>		
Drying Temperature		71 °C (160 °F)
Drying Time		6 hrs
Processing Melt Temperature		249-271 °C (480-520 °F)
Mold Temperature		16-38 °C (60-100 °F)

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

## Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform to the values given.

## Eastman Medical Disclaimer

It is the responsibility of the medical device manufacturer ("Manufacturer") to determine the suitability of all component parts and raw materials, including any Eastman product, used in its final product in order to ensure safety and compliance with requirements of the United States Food and Drug Administration (FDA) or other international regulatory agencies.

Eastman Chemical Company products have not been designed for nor are they promoted for end uses that would be categorized by either the United States FDA or by the International Standards Organization (ISO) as implant devices. Eastman products are not intended for use in the following applications: (1) in any bodily implant applications for greater than 30 days, based on FDA-Modified ISO-10993, Part 1 "Biological Evaluation of Medical Devices" tests (including any cosmetic, reconstructive or reproductive implant applications); (2) in any cardiac prosthetic device application, regardless of the length of time involved, including, without limitation, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass assisted devices, or (3) as any critical component in any medical device that supports or sustains human life.

Eastman Chemical Company products offered for the medical market have met selected FDA-Modified ISO-10993, Part 1 "Biological Evaluation of Medical Devices" tests with human tissue contact time of 30 days or less. The tests include: cytotoxicity, sensitization, irritation or intracutaneous reactivity, systemic toxicity (acute), subchronic toxicity (sub-acute), implantation, hemocompatibility. The Manufacturer is responsible for the biological evaluation of the finished medical device.

The suitability of an Eastman Product in a given end-use environment is dependent upon various conditions including, without limitation, chemical compatibility, temperature, part design, sterilization method, residual stresses, and external loads. It is the responsibility of the Manufacturer to evaluate its final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

---

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

2/28/2018 11:35:39 AM

