

Technical Data Sheet

Eastman™ DN501 Copolyester

Applications

- Appliances (food contact)
- Cabinetry
- Caps & lids non-food contact
- Chocolate molds
- Consumer housewares - food contact (fc)
- Decorative interiors
- Displays/in-store fixtures
- Fibers
- Furniture
- Graphic arts
- Indoor signs
- Industrial
- Lighting
- Point-of-purchase
- Transaction cards
- Visual merchandising
- Woodworking adhesive

Key Attributes

- Ability to mold thick parts
- Ease of processing
- Easy to extrude, cut, decorate, and seal
- Excellent clarity and color
- Excellent colorability
- Good impact strength
- Good stiffness
- High gloss appearance
- Improved gate aesthetics
- Readily fill intricate molds
- Toughness

Product Description

Eastman DN501 copolyester is a high flow product designed and engineered for many different applications. With its excellent color and clarity and its ability to mold thick parts with improved gate aesthetics, DN501 is clearly a well-suited copolyester for many applications. Other outstanding features are excellent chemical resistance, high gloss, and improvements in processing such as faster cycle times, and lower scrap rates. DN501 is also ideally suited for two-shot molding techniques due to its lower processing temperatures, very slow crystallization rate, and flow characteristics. Eastman DN501 contains a mold release derived from vegetable based sources.

Typical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.25 g/cm ³
Mold Shrinkage Parallel to Flow, 3.2-mm (0.125- in.) thickness	D 955	0.00450 mm/mm
Mechanical Properties (ISO Method)		
Haze	D 1003	0.55 %
Tensile Strength @ Yield	ISO 527	45 MPa (6526.69 psi)
Tensile Strength @ Break	ISO 527	28.2 MPa (4090.06 psi)
Transmittance	D 1003	90.80 %
Elongation @ Yield	ISO 527	4.9 %
Elongation @ Break	ISO 527	201.7 %
Tensile Modulus	ISO 527	1639.6 MPa (2.38 x 10 ⁵ psi)
Mechanical Properties		
Impact Resistance (Puncture), Energy @ Max. Load @ -40°C (-40°F)	D 3763	48.9 J (36.06 ft·lbf)
Tensile Modulus	D 638	1820 MPa (2.63 x 10 ⁵ psi)
Impact Resistance (Puncture), Energy @ Max. Load @ 23°C (73°F)	D 3763	36.2 J (26.69 ft·lbf) 50.5 MPa (7527.50 psi)

Tensile Stress @ Break	D 638	
Tensile Stress @ Yield	D 638	48.0 MPa (6874.79 psi)
Elongation @ Break	D 638	350.4 %
Elongation @ Yield	D 638	4.5 %
Flexural Yield Strength	D 790	68.94 MPa (9998.90 psi)
Flexural Modulus	D 790	1931.4 MPa (2.8 x 10 ⁵ psi)
Rockwell Hardness, R Scale	D 785	102.1
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	920 J/m (17.23 ft·lbf/in.)
@ -40°C (-40°F)	D 256	60.9 J/m (1.14 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	2840.3 J/m (53.21 ft·lbf/in.)
@ -40°C (-40°F)	D 4812	3168.5 J/m (59.36 ft·lbf/in.)
Thermal Properties		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	70.9 °C (159.6 °F)
@ 1.82 MPa (264 psi)	D 648	63.1 °C (145.6 °F)
Typical Processing Conditions		
Drying Temperature ^d		65-70 °C (149-158 °F)
Drying Time		6-8 hrs
Processing Melt Temperature		218-240 °C (424-464 °F)
Mold Temperature		16-38 °C (61-100 °F)

^aUnless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^bUnless noted otherwise, the test method is ASTM.

^cUnits are in SI or US customary units.

^dIn the event of the customer using a large dryer (greater than 8 feet tall) and pressure considerations, we recommend 65 C as the highest drying temperature, and for 8 hrs drying time

Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

5/29/2019 12:22:40 PM