

## Product Data Sheet

### Tenite™ Butyrate 485E3720023 Clear, Trsp

#### Application/Uses

- Appliances
- Consumer-Personal Care

#### Product Description

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers, or smoke transparents and black translucents. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Butyrate 485-23 contains an odor mask and an ultra-violet inhibitor(UVI). It has a plasticizer level of 23%.

#### Typical Properties

Property <sup>a</sup>	Test <sup>b</sup> Method	Typical Value, Units <sup>c</sup>
Plasticizer		23%
Specific Gravity	D 792	1.16
<b>Mechanical Properties</b>		
Tensile Stress @ Yield	D 638	17.2 MPa (2500 psi)
Tensile Stress @ Break	D 638	20.0 MPa (2900 psi)
Elongation @ Break	D 638	50%
Flexural Modulus	D 790	827 MPa (1.20 x 10 <sup>5</sup> psi )
Flexural Yield Strength	D 790	21.4 MPa (3100 psi)
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	448 J/m (8.4 ft·lbf/in.)
@ -40°C (-40°F)	D 256	123 J/m (2.3 ft·lbf/in.)
<b>Thermal Properties</b>		
Deflection Temperature <sup>d</sup>		
@ 1.82 MPa (264 psi)	D 648	52°C (126°F)
@ 0.455 MPa (66 psi)	D 648	68°C (154°F)
Vicat Softening Temperature <sup>d</sup>	D 1525	88°C (190°F)

<b>Permanence Properties</b>		
Water Absorption, 24 h immersion	D 570	1.2%
Soluble Matter Loss	D 570	0.1%
Weight Loss on Heating [72 hours @ 80°C (176°F)]	D 707	1.2%
<b>Miscellaneous Butyrate Properties</b>		
Refractive Index, $n_D$	D 542	1.46-1.49
Light Transmission <sup>e</sup>	E 308	>90%
Haze <sup>e</sup>	D 1003	<8.5%
Specific Heat @ 23°C (73°F)	DSC	1.26-1.67 kJ/kg·K (0.301-0.399 Btu/lb·°F)
Thermal Conductivity	C 177	0.17-0.33 W/m·K (1.2-2.3 Btu·in./h·ft <sup>2</sup> ·°F )
Coefficient of Linear Thermal Expansion	D 696	11-17 x 10 <sup>-5</sup> /°C (mm/mm·°C) (6-9 x 10 <sup>-5</sup> /°F (in./in.·°F))
Mold Shrinkage	D 955	0.2-0.6%
Dielectric Strength	D 149	11.8-18.7 kV/mm (300-475 V/mil)
Dielectric Constant 1 MHz	D 150	3.3-3.8
Dissipation Factor 1 MHz	D 150	0.01-0.15
Volume Resistivity	D 257	10 <sup>13</sup> -10 <sup>15</sup> ohm·cm

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

<sup>d</sup> Conditioned 4 hours @ 70°C (158°F)

<sup>e</sup> 1.52-mm (0.06-in.) specimen thickness

## Characteristics

Formula 485 - odor mask; UVI.

## Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

27-Jun-2001 3:19:00 PM