

## Product Data Sheet

### Tenite™ Propionate 307A2R30018, Natural, Trsp

#### Application/Uses

- Medical
- Ophthalmics

#### Product Description

Tenite™ cellulosic plastics are noted for their excellent balance of properties - toughness, hardness, strength, surface gloss, clarity, and a warm feel. The mechanical properties of Tenite™ cellulosic plastics differ with plasticizer levels. Lower plasticizer content yields a harder surface, higher heat resistance, greater rigidity, higher tensile strength, and better dimensional stability. Higher plasticizer content increases impact strength. Tenite™ cellulosic plastics are available in natural, clear, selected ambers or smoke transparents and black translucent. Color concentrates are available in let-down ratios from 10:1 to 40:1. Tenite™ Cellulose Acetate Propionate 307-18 contains an ultra-violet inhibitor and has a plasticizer level of 18%.

#### Typical Properties

| Property <sup>a</sup>               | Test <sup>b</sup> Method | Typical Value, Units <sup>c</sup>      |
|-------------------------------------|--------------------------|--|
| Plasticizer                         |                          | 18%                                    |
| Specific Gravity                    | D 792                    | 1.19                                   |
| <b>Mechanical Properties</b>        |                          |  |
| Tensile Stress @ Yield              | D 638                    | 22.1 MPa (3200 psi)                    |
| Tensile Stress @ Break              | D 638                    | 27.6 MPa (4000 psi)                    |
| Elongation @ Break                  | D 638                    | 35%                                    |
| Flexural Modulus                    | D 790                    | 1172 MPa (1.70 x 10 <sup>5</sup> psi ) |
| Flexural Yield Strength             | D 790                    | 29.0 MPa (4200 psi)                    |
| Rockwell Hardness, R Scale          | D 785                    | 55                                     |
| Izod Impact Strength, Notched       |                          |  |
| @ 23°C (73°F)                       | D 256                    | 523 J/m (9.8 ft·lbf/in.)               |
| @ -40°C (-40°F)                     | D 256                    | 107 J/m (2.0 ft·lbf/in.)               |
| <b>Thermal Properties</b>           |                          |  |
| Deflection Temperature <sup>d</sup> |                          |  |
| @ 1.82 MPa (264 psi)                | D 648                    | 67°C (153°F)                           |
| @ 0.455 MPa (66 psi)                | D 648                    | 77°C (171°F)                           |

| Permanence Properties                            |        |   |
|--|--------|---|
| Water Absorption, 24 h immersion                 | D 570  | 1.4%  |
| Soluble Matter Loss                              | D 570  | 0.1%  |
| Weight Loss on Heating [72 hours @ 80°C (176°F)] | D 1562 | 1.0%  |
| Miscellaneous Propionate Properties              |        |   |
| Refractive Index, n <sub>D</sub>                 | D 542  | 1.46-1.49   |
| Light Transmission <sup>e</sup>                  | E 308  | >90%  |
| Haze <sup>e</sup>                                | D 1003 | <8.5%   |
| Specific Heat @ 23°C (73°F)                      | DSC    | 1.26-1.67 kJ/kg·K (0.301-0.399 Btu/lb·°F)   |
| Thermal Conductivity                             | C 177  | 0.17-0.33 W/m·K (1.2-2.3 Btu·in./h·ft <sup>2</sup> ·°F )                          |
| Coefficient of Linear Thermal Expansion          | D 696  | 11-17 x 10 <sup>-5</sup> /°C (mm/mm·°C) (6-9 x 10 <sup>-5</sup> /°F (in./in.·°F)) |
| Mold Shrinkage                                   | D 955  | 0.2-0.6%  |
| Dielectric Strength                              | D 149  | 11.8-18.7 kV/mm (300-475 V/mil)   |
| Dielectric Constant 1 MHz                        | D 150  | 3.3-3.8   |
| Dissipation Factor 1 MHz                         | D 150  | 0.01-0.15   |
| Volume Resistivity                               | D 257  | 10 <sup>13</sup> -10 <sup>15</sup> ohm·cm   |

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

<sup>d</sup> Conditioned 4 hours @ 70°C (158°F)

<sup>e</sup> 1.52-mm (0.06-in.) thickness

Characteristics

Formula 307 - UVI

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.