

Technical Data Sheet

Eastman™ CP 349W Water-Reducible Chlorinated Polyolefin Adhesion Promoter

Applications

- Auto oem
- Auto plastics
- Auto refinish
- Automotive
- Automotive parts & accessories
- General industrial coatings
- Graphic arts
- Paints & coatings
- Truck/bus/rv

Product Description

Chlorinated polyolefin 349W is a water dispersion of a chlorinated polyolefin. It contains 2-amino-2-methyl-1-propanol as the neutralizing amine. The 2-amino-2-methyl-1-propanol in CP 349W makes it more compatible with other waterborne resins and therefore more useful as an additive.

Typical Properties

Property	Typical Value, Units
General	
Wt/Vol	1010-1040 g/L (8.4-8.7 lb/gal)
pH	
@ 25°C	9-10
Viscosity, Brookfield	10 cP
Solids	26 wt %
CPO	20 wt %
Chlorination ^a	18-23 %
Water	69 wt %
Organic Solvents ^b	5 wt %
Color, Gardner	Tan
Specific Gravity	
@ 25°C/25°C	1.026

^aApplies to the base polymer, not the dispersion itself.

^bContains ethylene glycol.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

