

# Technical Data Sheet

## Eastman Cadence™ Copolyester GS2

### Applications

- Building materials
- Decorative laminates-wood
- Doors
- Flooring
- Furniture
- Lenticular
- Point-of-purchase
- Transaction cards
- Wallpaper
- Walls
- Wood furniture

### Product Description

Eastman Cadence™ GS2 is a high-clarity amorphous copolyester for film calendering. Calendered films made of Eastman Cadence™ copolyesters are non-crystallizing, are halogen-free, offer wide calendering and thermoforming windows and have good low-temperature toughness. They are cooperative in secondary operations such as solvent-bonding, lamination, decoration, cold-forming, punching/cutting and embossment.

Eastman Cadence™ resins require no pre-drying or additional stabilizers.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®.

The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit [www.gei.com](#). Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

This product has been *CRADLE TO CRADLE CERTIFIED*™ Bronze, with Material Health Certificate, Platinum. The *CRADLE TO CRADLE CERTIFIED* mark is a registered certification mark used under license through the Cradle to Cradle Products Innovation Institute, a nonprofit organization that administers the publicly available *Cradle to Cradle Certified*™ Product Standard which provides designers and manufacturers with criteria and requirements for continually improving product materials and manufacturing processes. The *Cradle to Cradle Certified*™ Product Standard guides designers and manufacturers through a continual improvement process that looks at a product through five quality categories—material health, material reutilization, renewable energy and carbon management, water stewardship, and social fairness. A product receives an achievement level in each category—Basic, Bronze, Silver, Gold, or Platinum—with the lowest achievement level representing the product's overall mark.

The Material Health Certificate provides manufacturers with a trusted way to communicate their efforts to identify and replace chemicals of concern in their products. For more information about Cradle to Cradle certification and to obtain printable certificates for Eastman copolyesters, visit [www.cradletothecradle.com](#). Search for Eastman Chemical Company in *Cradle to Cradle Certified* Products Registry.

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>Electrical Properties</b>		
Dielectric Constant		
1 kHz	D 150	2.78

1 MHz	D 150	2.62
Dissipation Factor		
1 kHz	D 150	0.014
1 MHz	D 150	0.020
Arc Resistance	D 495	133 sec
Volume Resistivity	D 257	$3.32 \times 10^{16}$ ohm·cm
Surface Resistivity	D 257	$1.65 \times 10^{16}$ ohms/square
Dielectric Strength, Short Time, 500 V/sec rate-of-rise	D 149	15.6 kV/mm (396 V/mil)
<b>General Properties</b>		
Density	D 1505	1.28 g/cm <sup>3</sup>
Oxygen Index	D 2863	24.1 %
Water Absorption, 24 h immersion	D 570	0.15 %
<b>Thermal Properties</b>		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	71 °C (160 °F)
@ 1.82 MPa (264 psi)	D 648	64 °C (147 °F)
Vicat Softening Temperature	D 1525	81 °C (178 °F)
Coefficient of Linear Thermal Expansion		
@ -30°C to 30°C (-22°F to 86°F)	D 696	$7.68 \times 10^{-5}$ /°C (mm/mm·°C) (4.27 x 10 <sup>-5</sup> /°F (in./in.·°F))
Specific Heat		
@ 100°C (212°F)	DSC	1.7 kJ/kg·K (0.41 Btu/lb·°F)
@ 150°C (302°F)	DSC	1.8 kJ/kg·K (0.44 Btu/lb·°F)
@ 200°C (392°F)	DSC	2.0 kJ/kg·K (0.47 Btu/lb·°F)
@ 250°C (482°F)	DSC	2.1 kJ/kg·K (0.49 Btu/lb·°F)
@ 60°C (140°F)	DSC	1.3 kJ/kg·K (0.31 Btu/lb·°F)
Glass Transition Temperature (T <sub>g</sub> )	DSC	82 °C (180 °F)

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

## Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

2/28/2018 11:35:39 AM