

# Product Data Sheet

## Eastman Tritan™ Copolyester LX150HF

### Application/Uses

- Cosmetics hot-fill packaging
- Cosmetics/personal care packaging
- Fragrance packaging

### Key Attributes

- Ease of processing
- Excellent clarity
- Fast drying times
- Good chemical resistance
- Good heat resistance
- Improved flowability
- Outstanding impact resistance
- Quick cycle times

### Product Description

Eastman Tritan™ LX150HF is a high flow grade of an amorphous copolyester with excellent appearance and clarity. Eastman Tritan™ LX150HF has viscosity reductions of 40-50% relative to standard grades of Eastman Tritan™. Its most outstanding features are excellent toughness, hydrolytic stability, and heat and chemical resistance. Tritan™ LX150HF was developed for the cosmetic, fragrance, and personal care markets. Tritan™ LX150HF can easily be converted into articles for application in consumer and personal care markets by injection molding, extrusion blow molding, and injection blow molding.

### Typical Properties (Preliminary)

Property <sup>a</sup>	Test <sup>b</sup> Method	Typical Value, Units <sup>c</sup>
<b>General Properties</b>		
Specific Gravity	D 792	1.18
Mold Shrinkage	D 955	0.005-0.007 mm/mm (0.005-0.007 in./in.)
<b>Mechanical Properties</b>		
Tensile Stress @ Yield	D 638	43 MPa (6200 psi)
Tensile Stress @ Break	D 638	52 MPa (7500 psi)
Elongation @ Yield	D 638	7%
Elongation @ Break	D 638	210%
Tensile Modulus	D 638	1575 MPa (2.28 x 10 <sup>5</sup> psi )
Flexural Modulus	D 790	1575 MPa (2.28 x 10 <sup>5</sup> psi )
Flexural Yield Strength	D 790	64 MPa (9300 psi)
Rockwell Hardness, R Scale	D 785	111

**Izod Impact Strength, Notched**

@ 23°C (73°F)	D 256	860 J/m (16.1 ft·lbf/in.)
@ -40°C (-40°F)	D 256	110 J/m (2.1 ft·lbf/in.)

**Impact Strength, Unnotched**

@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB

**Impact Resistance (Puncture), Energy @ Max. Load**

@ 23°C (73°F)	D 3763	53 J (39 ft·lbf)
@ -40°C (-40°F)	D 3763	57 J (42 ft·lbf)

**Thermal Properties****Deflection Temperature**

@ 0.455 MPa (66 psi)	D 648	94°C (201°F)
@ 1.82 MPa (264 psi)	D 648	81°C (178°F)

**Optical Properties**

Total Transmittance	D 1003	91%
Haze	D 1003	<1%

**Typical Processing Conditions**

Drying Temperature	88°C (190°F)
Drying Time	4-6 hrs
Processing Melt Temperature	260-282°C (500-540°F)
Mold Temperature	38-66°C (100-150°F)

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

**Comments**

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

01-Apr-2009 8:01:26 AM