

# Product Data Sheet

## Eastman Tritan™ Copolyester LX500

### Application/Uses

- Cosmetics hot-fill packaging
- Cosmetics/personal care packaging
- Fragrance packaging

### Key Attributes

- Ease of processing
- Excellent clarity
- Fast drying times
- Good chemical resistance
- Good heat resistance
- Outstanding impact resistance
- Quick cycle times

### Product Description

Eastman Tritan™ LX500 is an amorphous copolyester specifically developed for use in blow molding applications for the cosmetic, fragrance, and personal care markets. Its most outstanding features are excellent toughness, hydrolytic stability, and heat and chemical resistance. In addition, this new generation copolyester offers excellent appearance and clarity.

### Typical Properties (Preliminary)

Property <sup>a</sup>	Test <sup>b</sup> Method	Typical Value, Units <sup>c</sup>
<b>General Properties</b>		
Specific Gravity	D 792	1.18
Mold Shrinkage	D 955	0.006 mm/mm (0.006 in./in.)
<b>Mechanical Properties</b>		
Tensile Stress @ Yield	D 638	45 MPa (6500 psi)
Tensile Stress @ Break	D 638	52 MPa (7600 psi)
Elongation @ Yield	D 638	7%
Elongation @ Break	D 638	139%
Tensile Modulus	D 638	1609 MPa (2.3x10 <sup>5</sup> psi)
Flexural Modulus	D 790	1522 MPa (2.2x10 <sup>5</sup> psi)
Flexural Yield Strength	D 790	64 MPa (9300 psi)
Rockwell Hardness, R Scale	D 785	110
Izod Impact Strength, Notched @ 23°C (73°F)	D 256	842 J/m (15.8 ft·lbf/in.)
Impact Strength, Unnotched @ 23°C (73°F)	D 4812	NB

**Impact Resistance (Puncture), Energy @ Max. Load**

@ 23°C (73°F)	D 3763	62 J (46 ft·lbf)
@ 0°C (32°F)	D 3763	65 J (48 ft·lbf)
@ -40°C (-40°F)	D 3763	67 J (49 ft·lbf)

**Mechanical Properties (ISO Method)**

Tensile Strength @ Yield	ISO 527	45 MPa
Tensile Stress @ Break	ISO 527	51 MPa
Elongation @ Yield	ISO 527	7%
Elongation @ Break	ISO 527	142%
Tensile Modulus	ISO 527	1569 MPa
Flexural Modulus	ISO 178	1494 MPa
Flexural Strength	ISO 178	60 MPa
Izod Impact Strength, Notched		
@ 23°C	ISO 180	78 kJ/m <sup>2</sup>
@ -40°C	ISO 180	12 kJ/m <sup>2</sup>

**Thermal Properties**

Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	101°C (214°F )
@ 1.82 MPa (264 psi)	D 648	85°C (185°F )

**Optical Properties**

Total Transmittance	D 1003	91%
Haze	D 1003	<1%

**Typical Processing Conditions**

Drying Temperature	88°C (190°F )
Drying Time	4-6 hrs
EBM Processing Melt Temperature	235-255°C (455-490°F)
EBM Blow Mold Temperature	15-50°C (60-122°F)
ISBM Processing Melt Temperature	260-280°C (500-536°F)
ISBM Injection Mold Temperature	40-65°C (104-149°F)
ISBM Blow Mold Temperature	35-55°C (95-131°F)

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

**Comments**

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and*

*completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

20-Aug-2013 10:01:49 AM