

Product Data Sheet

Eastman Tritan™ Copolyester TX1500HF

Application/Uses

- Appliances
- Consumer goods
- Durable goods
- Housewares

Key Attributes

- Ease of processing
- Excellent clarity
- Excellent hydrolytic stability
- Fast drying times
- Good chemical resistance
- Good flowability
- Good heat resistance
- Outstanding impact resistance
- Quick cycle times

Product Description

Eastman Tritan™ copolyester TX1500HF is a high flow grade of Eastman Tritan™. Eastman Tritan™ copolyester TX1500HF has viscosity reductions of 40-50% relative to Eastman Tritan™ copolyester TX1000. Other outstanding features include good toughness, hydrolytic stability, and heat and chemical resistance. Eastman Tritan™ copolyester TX1500HF may be used in repeated use food contact articles under United States Food and Drug Administration (FDA) regulations. Eastman Tritan™ copolyester TX1500HF is certified to NSF/ANSI Standard 51 for Food and Equipment Materials.

Typical Properties (Preliminary)

Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.18
Mold Shrinkage	D 955	0.005-0.007 mm/mm (0.005-0.007 in./in.)
Mechanical Properties		
Tensile Stress @ Yield	D 638	43 MPa (6200 psi)
Tensile Stress @ Break	D 638	52 MPa (7500 psi)
Elongation @ Yield	D 638	7%
Elongation @ Break	D 638	210%
Tensile Modulus	D 638	1575 MPa (2.28 x 10 ⁵ psi)
Flexural Modulus	D 790	1575 MPa (2.28 x 10 ⁵ psi)
Flexural Yield Strength	D 790	64 MPa (9300 psi)
Rockwell Hardness, R Scale	D 785	111

Izod Impact Strength, Notched @ 23°C (73°F)	D 256	860 J/m (16.1 ft·lbf/in.)
Impact Strength, Unnotched @ 23°C (73°F)	D 4812	NB

Mechanical Properties (ISO Method)

Tensile Strength @ Yield	ISO 527	44 MPa
Tensile Strength @ Break	ISO 527	49 MPa
Elongation @ Yield	ISO 527	7%
Elongation @ Break	ISO 527	154%
Tensile Modulus	ISO 527	1604 MPa
Flexural Modulus	ISO 178	1502 MPa
Flexural Strength	ISO 178	60 MPa
Izod Impact Strength, Notched @ 23°C	ISO 180	83 kJ/m ²
@ -40°C	ISO 180	11 kJ/m ²

Thermal Properties

Deflection Temperature @ 0.455 MPa (66 psi)	D 648	94°C (201°F)
@ 1.82 MPa (264 psi)	D 648	81°C (178°F)

Optical Properties

Total Transmittance	D 1003	91%
Haze	D 1003	<1%

Typical Processing Conditions

Drying Temperature	88°C (190°F)
Drying Time	4-6 hrs
Processing Melt Temperature	260-282°C (500-540°F)
Mold Temperature	38-66°C (100-150°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.