

Product Data Sheet

Eastman Tritan™ Copolyester TX2000

Application/Uses

- Appliances
- Consumer and durable goods
- Housewares
- Small appliances

Key Attributes

- Ease of processing
- Excellent clarity
- Excellent hydrolytic stability
- Fast drying times
- Good chemical resistance
- Good heat resistance
- Outstanding impact resistance
- Quick cycle times

Product Description

Eastman Tritan™ TX2000 is an amorphous copolyester with excellent appearance and clarity. Its most outstanding features are excellent toughness, hydrolytic stability, and heat and chemical resistance. This new-generation copolyester can also be molded into various applications without incorporating high levels of residual stress. Combined with Tritan™ copolyester's outstanding chemical resistance and hydrolytic stability, these features give molded products enhanced durability in the dishwasher environment, which can expose products to high heat, humidity, and aggressive cleaning detergents. Tritan™ TX2000 copolyester may be used in repeated use food contact articles under United States Food and Drug Administration (FDA) regulations. Tritan™ TX2000 copolyester is certified to NSF/ANSI Standard 51 for Food Equipment Materials.

Typical Properties (Preliminary)

Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.17
Mold Shrinkage	D 955	0.005-0.007 mm/mm (0.005-0.007 in./in.)
Mechanical Properties		
Tensile Stress @ Yield	D 638	44 MPa (6400 psi)
Tensile Stress @ Break	D 638	53 MPa (7700 psi)
Elongation @ Yield	D 638	7%
Elongation @ Break	D 638	140%
Tensile Modulus	D 638	1624 MPa (2.28 x 10 ⁵ psi)
Flexural Modulus	D 790	1585 MPa (2.28 x 10 ⁵ psi)

Flexural Yield Strength	D 790	66 MPa (9600 psi)
Rockwell Hardness, R Scale	D 785	115
Izod Impact Strength, Notched @ 23°C (73°F)	D 256	650 J/m (12.2 ft·lbf/in.)
Impact Strength, Unnotched @ 23°C (73°F)	D 4812	NB

Mechanical Properties (ISO Method)

Tensile Strength @ Yield	ISO 527	45 MPa
Tensile Strength @ Break	ISO 527	49 MPa
Elongation @ Yield	ISO 527	7%
Elongation @ Break	ISO 527	130%
Tensile Modulus	ISO 527	1624 MPa
Flexural Modulus	ISO 178	1531 MPa
Izod Impact Strength, Notched @ 23°C	ISO 180	66 kJ/m ²
@ -40°C	ISO 180	14 kJ/m ²

Thermal Properties

Deflection Temperature @ 0.455 MPa (66 psi)	D 648	109°C (228°F)
@ 1.82 MPa (264 psi)	D 648	92°C (198°F)

Optical Properties

Total Transmittance	D 1003	92%
Haze	D 1003	<1%

Typical Processing Conditions

Drying Temperature	88°C (190°F)
Drying Time	4-6 hrs
Processing Melt Temperature	260-282°C (500-540°F)
Mold Temperature	38-66°C (100-150°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.