

Product Data Sheet

Eastman Tritan™ Copolyester WX500

Application/Uses

- Extrusion blow molding
- Injection stretch blow molding
- Large refillable multi-use containers

Key Attributes

- Ease of processing
- Excellent clarity
- Excellent hydrolytic stability
- Good chemical resistance
- Good heat resistance
- Outstanding impact resistance

Product Description

Eastman Tritan™ WX500 is a resin specifically developed for blow molded bottles. Extremely high melt strength makes the resin an excellent choice when manufacturing large bottles. This new-generation copolyester most outstanding features are excellent toughness, hydrolytic stability, and heat and chemical resistance. Eastman Tritan™ WX500 copolyester may be used in repeated use food contact articles under United States Food and Drug Administration (FDA) regulations.

Typical Properties (Preliminary)

Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Specific Gravity	D 792	1.18
Mold Shrinkage	D 955	0.006 mm/mm (0.006 in./in.)
Mechanical Properties		
Tensile Stress @ Yield	D 638	45 MPa (6500 psi)
Tensile Stress @ Break	D 638	52 MPa (7600 psi)
Elongation @ Yield	D 638	7%
Elongation @ Break	D 638	139%
Tensile Modulus	D 638	1609 MPa (2.3x10 ⁵ psi)
Flexural Modulus	D 790	1522 MPa (2.2x10 ⁵ psi)
Flexural Yield Strength	D 790	64 MPa (9300 psi)
Rockwell Hardness, R Scale	D 785	110
Izod Impact Strength, Notched @ 23°C (73°F)	D 256	842 J/m (15.8 ft·lbf/in.)
Impact Strength, Unnotched @ 23°C (73°F)	D 4812	NB

Impact Resistance (Puncture), Energy @ Max. Load

@ 23°C (73°F)	D 3763	62 J (46 ft·lbf)
@ 0°C (32°F)	D 3763	65 J (48 ft·lbf)
@ -40°C (-40°F)	D 3763	67 J (49 ft·lbf)

Mechanical Properties (ISO Method)

Tensile Strength @ Yield	ISO 527	45 MPa
Tensile Strength @ Break	ISO 527	51 MPa
Elongation @ Yield	ISO 527	7%
Elongation @ Break	ISO 527	142%
Tensile Modulus	ISO 527	1569 MPa
Flexural Modulus	ISO 178	1494 MPa
Flexural Strength	ISO 178	60 MPa
Izod Impact Strength, Notched		
@ 23°C	ISO 180	78 kJ/m ²
@ -40°C	ISO 180	12 kJ/m ²

Thermal Properties

Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	101°C (214°F)
@ 1.82 MPa (264 psi)	D 648	85°C (185°F)

Optical Properties

Total Transmittance	D 1003	91%
Haze	D 1003	<1%

Typical Processing Conditions

Drying Temperature	88°C (190°F)
Drying Time	4-6 hrs
EBM Processing Melt Temperature	235-255°C (455-490°F)
EBM Blow Mold Temperature	15-50°C (60-122°F)
ISBM Processing Melt Temperature	260-280°C (500-536°F)
ISBM Injection Mold Temperature	40-65°C (104-149°F)
ISBM Blow Mold Temperature	35-55°C (95-131°F)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Applications

- Extrusion blow molding • Injection stretch blow molding

Comments

Properties reported here are based on limited testing of Tritan WX500. Eastman makes no representation that the material in any particular shipment will conform exactly to the values

given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

14-May-2012 8:05:14 AM