

Technical Data Sheet

Eastman™ Ester Gum 8D-M, Kosher

Applications

- Adhesives/sealants-b&c
- Bookbinding
- Caps & lids non-food contact
- Carpet construction
- Case & carton sealing closings
- Chewing gum
- Commerical printing inks
- Film modification
- Labels non food contact
- Packaging component films
- Packaging components non food contact
- Packaging tape
- Paints & coatings
- Polymer modification
- Protective coatings
- Road markings
- Roofing ingredients
- Solder flux
- Specialty tape
- Tape non food contact
- Tires
- Wax ingredients
- Wire/cable

Key Attributes

- Low acid number
- Low odor

Product Description

Eastman™ Ester Gum 8D-M kosher is a pale, thermoplastic glycerol ester of rosin. It is produced by means of a steam stripping process that yields a low-odor and low color resin suitable for food ingredient application. This resin is produced from glycerin from non-animal origin and gum rosin harvested from pine trees. All kosher products produced by Eastman are manufactured under rabbinical supervision in full accordance with Jewish dietary law.

Typical Properties

Property	Test Method	Typical Value, Units
General		
Acid Number (mg KOH/g)		5
Ring and Ball Softening Point	ASTM E 28	85 °C
Color, Gardner ^a		4+
Taste Test (5% in water)		No flavor
Appearance		Crystalline Solid
Description, Base Resin		Rosin

^a50% resins solids in toluene or xylene

Compatibility and Solubility

Eastman™ Ester Gum 8D-M kosher is compatible in all proportions, or in limited but practically useful concentrations with SBR copolymers, ethyl cellulose, polystyrene, natural and synthetic rubbers, natural or

synthetic resins, waxes and most vinyl polymers. It is soluble in esters, ketones, high molecular weight alcohol, and aliphatic and aromatic hydrocarbon solvents. It is insoluble in methanol, ethanol and water.

Packaging

Eastman™ Ester Gum 8D-M kosher is packaged in 25 kgs polyethylene bags in pastilles, shipped from Eastman's facilities in Uruapan Michoacán in Mexico.

Storage

The resin is provided in pastilles which may fuse, block or lump under any of the following conditions: 1) in hot weather climate 2) if stored near steam pipes or other sources of heat; 3) upon prolonged storage; 4) storage in stacks more than three pallets high, or in any combination of these conditions. Storage at temperature above 30°C should be avoided as these conditions will greatly accelerate the fusion of the product. Inside storage in a temperature-controlled area is recommended in order to minimize product fusion.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse affect on the solubility of the resin in organic solvents or in its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Eastman™ Ester Gum 8D-M kosher will remain within product specification limits as mentioned under the heading "Product Specifications", for a period of 1 year from production date and if storage conditions outlined in this data sheet are observed.

However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which is used, we recommend that the material be tested upon receipt.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

2/28/2018 11:35:39 AM