

# Technical Data Sheet

## Eastman Neostar™ Elastomer FN006

### Applications

- Automotive
- Compounders
- Equipment & machinery
- Fishing line
- Profiles

### Key Attributes

- Environmentally preferred, non-halogenated material
- Excellent chemical resistance
- Exceptional heat resistance and high temperature dimensional stability
- High flexibility without plasticizers
- Solvent bondable

### Product Description

Eastman Neostar™ Elastomer FN006 is the second in Eastman's series of tough, clear, durable, general purpose grade copolyester ethers. Developed for use in the profile and automotive markets, it can also be used in packaging and tubing applications. Its chemical resistance, flexibility, and toughness make it an ideal choice for applications where strength, durability, and puncture resistance in harsh environments is required. Eastman Neostar™ Elastomer FN006 can be used in injection molding or cast film, blown film, or tubing extrusion applications. This copolyester has a full range of flexibility and memory without the addition of plasticizers. Considered environmentally preferred due to its non-halogenated material composition, it can be incinerated cleanly without the emission of toxic gases. The target inherent viscosity of this product is 1.6.

This product has been *CRADLE TO CRADLE CERTIFIED*™ Bronze, with Material Health Certificate, Platinum. The *CRADLE TO CRADLE CERTIFIED* mark is a registered certification mark used under license through the Cradle to Cradle Products Innovation Institute, a nonprofit organization that administers the publicly available *Cradle to Cradle Certified*™ Product Standard which provides designers and manufacturers with criteria and requirements for continually improving product materials and manufacturing processes. The *Cradle to Cradle Certified*™ Product Standard guides designers and manufacturers through a continual improvement process that looks at a product through five quality categories—material health, material reutilization, renewable energy and carbon management, water stewardship, and social fairness. A product receives an achievement level in each category—Basic, Bronze, Silver, Gold, or Platinum—with the lowest achievement level representing the product's overall mark.

The Material Health Certificate provides manufacturers with a trusted way to communicate their efforts to identify and replace chemicals of concern in their products. For more information about Cradle to Cradle certification and to obtain printable certificates for Eastman copolyesters, visit [Eastman Chemical Company in Cradle to Cradle Certified Products Registry](#).

### Typical Properties

Property <sup>a</sup>	Test Method <sup>b</sup>	Typical Value, Units <sup>c</sup>
<b>Mechanical Properties</b>		
Specific Gravity	D 792	1.13
Durometer Hardness		
Shore A Scale	D 2240	95
Shore D Scale	D 2240	55
Tensile Stress @ Break <sup>d</sup>	D 638	22 MPa (3200 psi)
Tensile Stress @ Yield <sup>e</sup>	D 638	14 MPa (2030 psi)
Elongation @ Yield	D 638	38 %
Elongation @ Break	D 638	400 %
Tensile Modulus	D 638	170 MPa (24650 psi)
Flexural Modulus	D 790	150 MPa (21750 psi)
Tear Strength	D 1004	350 N (79 lbf)

Izod Impact Strength, Notched @ -40°C (-40°F)	D 256	40 J/m (0.75 ft·lbf/in.)
Torsional Modulus Temperature @ 240 MPa (35,000 psi)	D 1043	-28 °C (-18 °F)
@ 930 MPa (135,000 psi)	D 1043	<-70 °C (<-94 °F)
Water Absorption, 24 h immersion	D 570	0.4 %
<b>Thermal Properties</b>		
Inherent Viscosity	EMN-A-AC-G-V-1	1.16
Flow Rate (Condition 215°C/2.16 kg)	D 1238	11 g/10 min
(Condition 230°C/2.16 kg)	D 1238	18 g/10 min
Crystalline Peak Melting Point (T <sub>m</sub> )	D 3418	205 °C (400 °F)
Crystallization Temperature on Cooling (T <sub>c</sub> )	DSC	140 °C (284 °F)
Glass Transition Temperature (T <sub>g</sub> )	DSC	-40 °C (-40 °F)
Specific Heat <sup>f</sup> @ 100°C (212°F) - solid	DSC	1.8 kJ/kg·K (0.43 Btu/lb·°F)
@ 150°C (302°F) - solid	DSC	2.0 kJ/kg·K (0.48 Btu/lb·°F)
@ 175°C (347°F) - solid	DSC	2.3 kJ/kg·K (0.55 Btu/lb·°F)
@ 200°C (392°F) - transition	DSC	3.1 kJ/kg·K (0.74 Btu/lb·°F)
@ 225°C (437°F) - melt	DSC	2.3 kJ/kg·K (0.55 Btu/lb·°F)
@ 25°C (77°F) - solid	DSC	1.6 kJ/kg·K (0.38 Btu/lb·°F)
Heat of Fusion	E 793	27 kJ/kg (11.6 Btu/lb)
Thermal Conductivity	C 177	0.19 W/m·K (1.3 Btu·in./h·ft <sup>2</sup> ·°F)
Coefficient of Linear Thermal Expansion	D 696	15 x 10 <sup>-5</sup> /°C (mm/mm·°C) (8 x 10 <sup>-5</sup> /°F (in./in.·°F))
Brittleness Temperature	D 746	<-75 °C (<-103 °F)
Vicat Softening Temperature @ 1 kg load	D 1525	170 °C (338 °F)

<sup>a</sup>Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup>Unless noted otherwise, the test method is ASTM.

<sup>c</sup>Units are in SI or US customary units.

<sup>d</sup>D 412, Die C specimens, which are equivalent to ASTM D 638, Type IV specimens. Specimens were 2.0 mm (0.075 in.) thick and were tested using a crosshead speed of 500 mm (20 in.) per min.

<sup>e</sup>Injection molded ASTM D 638 Type I specimens, about 3 mm (1/8 in.) thick, were tested using a crosshead speed of 500 mm (20 in.) per min.

<sup>f</sup>For 200°C (392°F) - transition, apparent specific heat, including the effects of the heat of fusion.

## Applications

NEOSTAR elastomers are tough, clear and durable. NEOSTAR elastomer FN006 can be injection molded or extruded. It has a property profile that is suitable for automotive applications such as trim and constant velocity or steering boots. It is especially suitable for coextrusion as a flexible element in profile extrusions.

## Comments

Properties reported here are based on limited testing. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

*Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

