



Product Data Sheet

Eastman Provista™ Copolymer ST

Application/Uses

- Packaging tubes
- Plastic angle moldings
- Pricing channels
- Profiles
- Signage channels
- Store fixtures

Key Attributes

- Ease of processing
- Excellent chemical resistance
- Meets FDA regulations for food contact
- Sparkling clarity and high gloss
- Toughness with flexibility

Product Description

Eastman Provista™ Copolymer ST is a resin specifically developed for profile extrusion where high clarity and gloss, toughness, and processability are critical. Eastman Provista™ Copolymer ST is a second-generation material that complements Eastman Provista™ by offering similar features, while providing greater toughness. Eastman Provista™ Copolymer ST is ideal in applications that place greater physical demands on the profile.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®. The GREENGUARD INDOOR AIR QUALITY CERTIFIED® Mark is a registered certification mark used under license through the GREENGUARD Environmental Institute (GEI). GEI is an industry-independent, non-profit organization that oversees the GREENGUARD Certification Program. The GREENGUARD Certification Program is an industry independent, third-party testing program for low-emitting products and materials for indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit www.greenguard.org. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

Typical Properties

Property ^a	Test ^b Method	Typical Value, Units ^c
General Properties		
Density	D 792	1.25 g/cm ³
Mold Shrinkage	D 955	0.3%
Mechanical Properties		
Tensile Stress @ Yield	D 638	47 MPa (6900 psi)
Tensile Stress @ Break	D 638	48 MPa (7000 psi)
Elongation @ Yield	D 638	5%
Elongation @ Break	D 638	300%
Tensile Modulus	D 638	1900 MPa (2.7 x 10 ⁵ psi)

Flexural Modulus	D 790	1900 MPa (2.7 x 10 ⁵ psi)
Flexural Strength	D 790	65 MPa (9400 psi)
Rockwell Hardness, R Scale	D 785	105
Izod Impact Strength, Notched ^d		
@ 23°C (73°F)	D 256	NB
@ -40°C (-40°F)	D 256	63C J/m (1.2C ft·lbf/in.)
Impact Strength, Unnotched ^e		
@ 23°C (73°F)	D 4812	NB
@ -40°C (-40°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	41 J (30 ft·lbf)
@ 0°C (32°F)	D 3763	41 J (30 ft·lbf)
@ -40°C (-40°F)	D 3763	39 J (29 ft·lbf)

Thermal Properties

Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	73°C (163°F)
@ 1.82 MPa (264 psi)	D 648	63°C (145°F)
Vicat Softening Temperature	D 1525	85°C (185°F)

Optical Properties

Haze	D 1003	1.3%
Gloss @ 60°	D 2457	143
Regular Transmittance	D 1003	87%
Total Transmittance	D 1003	91%
Color		
L*	D 2244	95.0
a*	D 2244	-0.2
b*	D 2244	0.6

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

^d C = Complete Break; Nonbreak as defined by ASTM D 256.

^e Nonbreak as defined by ASTM D 4812.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.